

**SECTION 1. Identification of the substance/preparation and of the company/undertaking**

Manufacturer: E.I. du Pont de Nemours & Co.  
 DuPont Performance Coatings  
 Wilmington, DE, 19898

Telephone: Product information: (800) 441-7515  
 Medical emergency: (800) 441-3637  
 Transportation emergency: (800) 424-9300  
 (CHEMTREC)

Product: **ChromaBase® Factory Packaged Colors**

DOT Shipping Name: See DOT Addendum.

Hazardous Materials Information: See Section 10.

INGREDIENTS	CAS #	VAPOR PRESSURE	EXPOSURE LIMITS
Butyl acetate	123-86-4	10.0	Respirable Dust D 3.0 mg/m3 Respirable Dust
C.i. pigment red 254	84632-65-5	None	A 200.0 ppm 15 min STEL A 150.0 ppm O 150.0 ppm
Carbamate resin	26935-10-4	None	A None O None
Carbon black	1333-86-4	None	A 3.5 mg/m3 O 3.5 mg/m3 D 0.5 mg/m3 8 & 12 hour TWA
Cellulose acetate butyrate	9004-36-8	None	A None O None
Ethylbenzene	100-41-4	7.0	A 125.0 ppm 15 min STEL A 100.0 ppm O 100.0 ppm D 25.0 ppm 8 & 12 hour TWA

Copyright 2007 E. I. duPont de Nemours and Company. All rights reserved. Copies may be made only for those using DuPont products.

**SECTION 2. Composition/information on ingredients**

INGREDIENTS	CAS #	VAPOR PRESSURE	EXPOSURE LIMITS
Acetone	67-64-1	247.0@68.0°F	A 750.0 ppm 15 min STEL A 500.0 ppm O 1000.0 ppm D 500.0 ppm 8 & 12 hour TWA
Acrylic polymer	96591-17-2	None	A None O None
Aluminum	7429-90-5	None	A 10.0 mg/m3 particulate A 5.0 mg/m3 Dust O 15.0 mg/m3 Total Dust O 5.0 mg/m3 Respirable Dust
Aluminum hydroxide	21645-51-2	None	A None O None
Aluminum oxide	1344-28-1	None	A 10.0 mg/m3 O 15.0 mg/m3 Total Dust O 5.0 mg/m3 Respirable Dust
Amorphous silica	7631-86-9	None	A 10.0 mg/m3 Total Dust O 20.0 mppcf D 3.0 mg/m3
Amorphous silica - precipitated	112926-00-8	None	A 10.0 mg/m3 O 15.0 mg/kg Total Dust O 5.0 mg/m3 TWA
Hydrotreated heavy naphtha (petroleum)	64742-48-9	3.3@68.0°F	A None O None
Iron oxide	1309-37-1	None	A 5.0 mg/m3 Respirable Dust O 10.0 mg/m3 D 3.0 mg/m3
Isobutyl alcohol	78-83-1	9.7@22.0°C	A 50.0 ppm O 100.0 ppm
Melamine resin	68955-24-8	25.0	A None O None
Methyl ethyl ketone	78-93-3	71.2	A 300.0 ppm 15 min STEL A 200.0 ppm O 200.0 ppm D 300.0 ppm 15 min TWA D 200.0 ppm 8 & 12 hour TWA
Mica	12001-26-2	None	A 3.0 mg/m3 Respirable Dust O 20.0 mppcf O 3.0 mg/m3 Respirable Dust
N-pentyl propionate	624-54-4	1.5	A None O None
Perylene maroon	5521-31-3	None	A None O None

INGREDIENTS	CAS #	VAPOR PRESSURE	EXPOSURE LIMITS	INGREDIENTS	CAS #	VAPOR PRESSURE	EXPOSURE LIMITS
Perylene pigment	5521-31-3	None	A 10.0 mg/m3 O None		108-88-3	22.0	A 20.0 ppm
Phthalocyanine green	1328-53-6	None	A 3.0 mg/m3 TWA Respirable Dust A 10.0 mg/m3 TWA inhalable dust O 15.0 mg/m3 TWA Total Dust O 5.0 mg/m3 TWA Respirable Dust	Xylene	1330-20-7	8.0@25.0°C	O 300.0 ppm CEIL O 500.0 ppm 10 min TWA O 200.0 ppm D 50.0 ppm 8 & 12 hour TWA A 150.0 ppm 15 min STEL A 100.0 ppm O 100.0 ppm D 150.0 ppm 15 min STEL D 100.0 ppm 8 & 12 hour TWA
Pigment red 202	3089-17-6	None	A 3.0 mg/m3 Respirable Dust A 10.0 mg/m3 inhalable dust PNOR O 5.0 mg/m3 Respirable Dust PNOR O 15.0 mg/m3	*A=ACGIH, O=OSHA, D=DuPont, S=Suppliers. Limits are 8 hour TWA unless otherwise specified. Vapor pressure @ 20° C unless otherwise noted.			
Polyester resin	35561-07-0	None	A None O None	<b>SECTION 3. Hazards identification</b>			
Polyethylene/vinyl acetate	24937-78-8	None	A None O None	<b>Potential Health Effects:</b>			
Quinacridone pigment	1047-16-1	None	A 10.0 mg/m3 inhalable dust A 3.0 mg/m3 O 15.0 mg/m3 Total Dust PNOR O 5.0 mg/m3 Respirable Dust D 10.0 mg/m3 Total Dust	<b>Inhalation:</b> May cause nose and throat irritation. May cause nervous system depression, characterized by the following progressive steps: headache, dizziness, nausea, staggering gait, confusion, unconsciousness. Reports have associated repeated and prolonged overexposure to solvents with permanent brain and nervous system damage. If this product contains or is mixed with an isocyanate activator/hardener, the following health effects may apply: Exposure to isocyanates may cause respiratory sensitization. This effect may be permanent. Symptoms include an asthma-like reaction with shortness of breath, wheezing, cough or permanent lung sensitization. This effect may be delayed for several hours after exposure. Repeated overexposure to isocyanates may cause a decrease in lung function, which may be permanent. Individuals with lung or breathing problems or prior reactions to isocyanates must not be exposed to vapors or spray mist of this product.			
Silica alumina ceramic	66402-68-4	None	A None O None	<b>Ingestion:</b> May result in gastrointestinal distress.			
Stoddard solvent	8052-41-3	1.0@25.0°C	A 100.0 ppm O 500.0 ppm TWA D 100.0 ppm 15 min STEL D 50.0 ppm 8 & 12 hour TWA	<b>Skin or eye contact:</b> May cause irritation or burning of the eyes. Repeated or prolonged liquid contact may cause skin irritation with discomfort and dermatitis.			
Titanium dioxide	13463-67-7	None	A 10.0 mg/m3 O 15.0 mg/m3 Total Dust D 10.0 mg/m3 Total Dust D 5.0 mg/m3 Respirable Dust	<b>Other Potential Health Effects in addition to those listed above:</b> <b>Acetone</b> The following medical conditions may be aggravated by exposure: lung disease, eye disorders, skin disorders. Overexposure may cause damage to any of the following organs/systems: blood, central nervous system, eyes, kidneys, liver, respiratory system, skin.			
Toluene				<b>Butyl acetate</b> May cause abnormal liver function. The following medical conditions may be aggravated by exposure: respiratory system. Tests for embryotoxic activity in animals has been inconclusive. Rats exposed to very high airborne levels have exhibited high frequency hearing deficits. The significance of this to man is unknown. Has been toxic to the fetus in laboratory animals at doses that are toxic to the mother.			
				<b>Carbon black</b>			

Is an IARC, NTP or OSHA carcinogen. Has shown carcinogenic activity in laboratory animals at high doses. Significance to man is unknown. The following medical conditions may be aggravated by exposure: asthma, respiratory disease.

WARNING: This chemical is known to the State of California to cause cancer.

#### Ethylbenzene

Is an IARC, NTP or OSHA carcinogen. Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of the following: central nervous system, kidneys, liver, lungs.

Recurrent overexposure may result in liver and kidney injury. Studies in laboratory animals have shown reproductive, embryotoxic and developmental effects.

WARNING: This chemical is known to the State of California to cause cancer.

#### Hydrotreated heavy naphtha (petroleum)

Laboratory studies with rats have shown that petroleum distillates can cause kidney damage and kidney or liver tumors. These effects were not seen in similar studies with guinea pigs, dogs, or monkeys. Several studies evaluating petroleum workers have not shown a significant increase of kidney damage or an increase in kidney or liver tumors.

#### Isobutyl alcohol

Has shown carcinogenic activity in laboratory animals at high doses. Significance to man is unknown. May cause irritation of the mucous membranes. May cause abnormal liver function. Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of the following: eyes, respiratory system, skin. Tests in laboratory animals have shown effects on any of the following organs/systems: bone marrow, liver. Prolonged skin contact may cause chemical burns. Liquid splashes in the eye may result in chemical burns.

#### Melamine resin

This chemical is a formaldehyde donor. Formaldehyde is an IARC, NTP or OSHA carcinogen and has shown mutagenic activity in laboratory cell culture tests. May induce pulmonary sensitization or significant irritation of the respiratory airways. Formaldehyde has produced tumors in the nasal passages of laboratory animals when exposed to high concentrations for a two year period. IARC has concluded epidemiology studies found evidence of formaldehyde related nasopharyngeal cancer in humans and have classified formaldehyde as a confirmed human carcinogen. DuPont toxicologists have reviewed these studies and classified formaldehyde as a possible human carcinogen.

#### Methyl ethyl ketone

Material is irritating to mucous membranes and upper respiratory tract. Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of the following: central nervous system, eyes, respiratory system, skin. Prolonged or repeated overexposure may cause any of the following: conjunctivitis, dermatitis. High concentrations have caused embryotoxic effects in laboratory animals. Aspiration may occur during swallowing or vomiting, resulting in lung damage. Ingestion may cause headache, nausea, vomiting, dizziness, and drowsiness.

#### Mica

Repeated or prolonged inhalation may cause any of the following: lung irritation. Long-term respiratory exposure exceeding TLV may damage the lungs, leading to bronchitis and impairment of lung capacity.

#### Silica alumina ceramic

Ingestion may cause any of the following: gastrointestinal irritation. Skin or eye contact may cause any of the following: mechanical irritation. Inhalation may cause any of the following: upper respiratory tract irritation.

#### Stoddard solvent

The following medical conditions may be aggravated by exposure: asthma, skin disorders. Laboratory studies with rats have shown that petroleum distillates can cause kidney damage and kidney or liver tumors. These effects were not seen in similar studies with guinea pigs, dogs, or monkeys.

Several studies evaluating petroleum workers have not shown a significant increase of kidney damage or an increase in kidney or liver tumors.

#### Titanium dioxide

Is an IARC, NTP or OSHA carcinogen. In a lifetime inhalation test, lung cancers were found in some rats exposed to 250 mg/m<sup>3</sup> respirable titanium dust. Analysis of the titanium dioxide concentrations in the rat's lungs showed that the lung clearance mechanism was overwhelmed and that the results at the massive 250 mg/m<sup>3</sup> level are not relevant to the workplace. Results of a DuPont epidemiology study showed that employees who had been exposed to Titanium Dioxide were at no greater risk of developing lung cancer than were employees who had not been exposed to Titanium dioxide. No pulmonary fibrosis was found in any of the employees and no association was observed between Titanium dioxide exposure and chronic respiratory disease or x-ray abnormalities. Based on the results of this study DuPont concludes that titanium dioxide will not cause lung cancer or chronic respiratory disease in humans at concentrations experienced in the workplace.

#### Toluene

Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of the following: central nervous system, kidneys, liver, respiratory system, skin. Can be absorbed through the skin in harmful amounts. Recurrent overexposure may result in liver and kidney injury. High airborne levels have produced irregular heart beats in animals and occasional palpitations in humans. Rats exposed to very high airborne levels have exhibited high frequency hearing deficits. The significance of this to man is unknown.

WARNING: This chemical is known to the State of California to cause birth defects or other reproductive harm.

#### Xylene

Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of the following: bone marrow, cardiovascular system, central nervous system, kidneys, liver, lungs. Recurrent overexposure may result in liver and kidney injury. High exposures may produce irregular heart beats. Canada classifies Xylene as a developmental toxin as high exposures to xylenes in some animal studies have been reported to cause health effects on the developing fetus/embryo. These effects were often at levels toxic to the adult animal. The significance of these effects to humans is not known. Repeated or prolonged skin contact may cause any of the following: irritation, dryness, cracking of the skin.

## SECTION 4. First aid measures

### First Aid Procedures:

#### Inhalation:

If affected by inhalation of vapor or spray mist, move to fresh air. If not breathing, give artificial respiration, preferably mouth-to-mouth. If breathing difficulty persists, or occurs later, consult a physician.

#### Ingestion:

In the unlikely event of ingestion, DO NOT INDUCE VOMITING. Call a physician immediately and have names of ingredients available.

#### Skin or eye contact:

In case of eye contact, immediately flush with plenty of water for at least 15 minutes; call a physician. In case of skin contact, wash thoroughly with soap and water. If irritation occurs, contact a physician.

## SECTION 5. Fire-fighting measures

**Flash Point (Closed Cup):** See Section 11 for exact values.

**Flammable Limits:** LFL 1 % UFL 13 %

**Extinguishing Media:**

Universal aqueous film-forming foam, carbon dioxide, dry chemical.

**Fire Fighting Procedures:**

Full protective equipment, including self-contained breathing apparatus, is recommended. Water from fog nozzles may be used to prevent pressure build-up.

**Fire and Explosion Hazards:**

For flammable liquids, vapor/air will ignite when an ignition source is present. In other cases, when heated above the flash point, emits flammable vapors which, when mixed with air, can burn or be explosive. Fine mists or sprays may be flammable at temperatures below the flash point.

**SECTION 6. Accidental release measures**

**Procedures for cleaning up spills or leaks:**

Ventilate area. Remove sources of ignition. Prevent skin and eye contact and breathing of vapor. If material does not contain or is not mixed with an isocyanate activator/hardener: Wear a properly fitted air-purifying respirator with organic vapor cartridges (NIOSH approved TC-23C), eye protection, gloves and protective clothing. Confine, remove with inert absorbent, and dispose of properly. If the material contains, or is mixed with an isocyanate activator/hardener: Wear a positive-pressure, supplied-air respirator (NIOSH approved TC-19C), eye protection, gloves and protective clothing. Pour liquid decontamination solution over the spill and allow to sit at least 10 minutes. Typical decontamination solutions for isocyanate containing materials are: 20% Surfactant (Tergitol TMN 10) and 80% Water OR 0-10% Ammonia, 2-5% Detergent and Water (balance). Pressure can be generated. Do not seal waste containers for 48 hours to allow CO2 to vent. After 48 hours, material may be sealed and disposed of properly.

**Ecological information:**

There is no data available on the product. The product should not be allowed to enter drains, water courses or the soil.

**SECTION 7. Handling and storage**

**Precautions to be taken in handling and storing:**

Observe label precautions. If combustible (flashpoint between 100 - 200 deg F), keep away from heat, sparks and flame. If flammable (flashpoint less than 100 deg F), also keep away from static discharges and other sources of ignition. If material is extremely flammable (flashpoint less than 20 deg F) or flammable, VAPORS MAY IGNITE EXPLOSIVELY OR CAUSE FLASH FIRE, respectively. Vapors may spread long distances. Prevent buildup of vapors. Close container after each use. Ground containers when pouring. Wash thoroughly after handling and before eating or smoking. Do not store above 120 deg F. If product is waterbased, do not freeze.

**Other precautions:**

If material is a coating: do not sand, flame cut, braze or weld dry coating without a NIOSH approved air purifying respirator with particulate filters or appropriate ventilation, and gloves.

**SECTION 8. Exposure controls / personal protection**

**Engineering controls and work practices:**

**Ventilation:**

Provide sufficient ventilation in volume and pattern to keep contaminants below applicable exposure limits.

**Respiratory protection:**

Do not breathe vapors or mists. If this product contains isocyanates or is used with an isocyanate activator/hardener, wear a positive-pressure, supplied-air respirator (NIOSH approved TC-19C) while mixing activator/hardener with paint, during application and until all vapors and spray mist are exhausted. If product does not contain or is not mixed with an isocyanate activator/hardener, a properly fitted air-purifying respirator with organic vapor cartridges (NIOSH TC-23C) and particulate filter (NIOSH TC-84A) may be used. Follow respirator manufacturer's directions for respirator use. Do not permit anyone without protection in the painting area. Individuals with history of lung or breathing problems or prior reaction to isocyanates should not use or be exposed vapor or spray mist if product contains or is mixed with isocyanate activators/hardeners.

**Protective equipment:**

Personal protective equipment should be worn to prevent contact with eyes, skin or clothing.

**Skin protection:**

Neoprene gloves and coveralls are recommended.

**Eye protection:**

Desirable in all industrial situations. Goggles are preferred to prevent eye irritation. If safety glasses are substituted, include splash guard or side shields.

**SECTION 9. Physical and chemical properties**

Evaporation rate	Slower than Ether
Water solubility	NIL
Vapour density	Heavier than air
Approx. Boiling Range ( °C)	55.6 - 399 °C
Approx. Freezing Range ( °C)	-93.3 - -35 °C
Gallon Weight (lbs/gal)	7.65 - 10.4
Specific Gravity	0.92 - 1.25
Percent Volatile By Volume	69.34 - 82.94
Percent Volatile By Weight	48.14 - 77.94
Percent Solids By Volume	17.06 - 30.66
Percent Solids By Weight	22.06 - 51.86

**SECTION 10. Stability and reactivity**

**Stability:**

Stable

**Incompatibility (materials to avoid):**

None reasonably foreseeable

**Hazardous decomposition products:**

CO, CO2, smoke, and oxides of any heavy metals that are reported in "Composition, Information on Ingredients" section.

**Hazardous Polymerization:**

Will not occur.

**Sensitivity to Static Discharge:**

For flammable materials (flashpoint less than 100 deg F) and combustibles (flashpoint between 100-200 deg F) if heated above the flashpoint, solvent vapors in air may explode if static grounding and bonding is not used during transfer of this product.

**Sensitivity to Mechanical Impact:**

None known.

**SECTION 11. Additional Information**

**99K™** Acrylic polymer, Butyl acetate, Carbon black(2.4%), Cellulose acetate butyrate, Ethylbenzene(2.7%\*), Methyl ethyl ketone, N-pentyl propionate, Toluene(24%\*), Xylene(7%\*)  
**GAL WT: 7.81 WT PCT SOLIDS: 32.28 VOL PCT SOLIDS: 25.98**  
**SOLVENT DENSITY: 7.15 VOC LE: 5.3 VOC AP: 5.3**  
**FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: YES**

**100990K™** Acetone, Acrylic polymer, Butyl acetate, Carbamate resin, Cellulose acetate butyrate, Ethylbenzene(5.5%\*), Hydrotreated heavy naphtha (petroleum), Isobutyl alcohol, Melamine resin, Polyester resin, Polyethylene/vinyl acetate, Xylene(20%\*)  
**GAL WT: 7.68 WT PCT SOLIDS: 24.15 VOL PCT SOLIDS: 18.81**  
**SOLVENT DENSITY: 7.18 VOC LE: 5.7 VOC AP: 5.1**  
**FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: YES**

**101756K™** Acetone, Acrylic polymer, Aluminum oxide(1%\*), Butyl acetate, Carbamate resin, Carbon black(0.4%), Cellulose acetate butyrate, Ethylbenzene(5.3%\*), Isobutyl alcohol, Melamine resin, Polyester resin, Polyethylene/vinyl acetate, Titanium dioxide(0.8%), Xylene(19%\*)  
**GAL WT: 7.76 WT PCT SOLIDS: 25.12 VOL PCT SOLIDS: 19.16**  
**SOLVENT DENSITY: 7.20 VOC LE: 5.7 VOC AP: 5.1**  
**FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: YES**

**736625K™** Acetone, Acrylic polymer, Aluminum(1%\*), Butyl acetate, Carbamate resin, Cellulose acetate butyrate, Ethylbenzene(5.5%\*), Hydrotreated heavy naphtha (petroleum), Iron oxide, Isobutyl alcohol, Polyester resin, Polyethylene/vinyl acetate, Xylene(19%\*)  
**GAL WT: 7.76 WT PCT SOLIDS: 25.40 VOL PCT SOLIDS: 19.31**  
**SOLVENT DENSITY: 7.19 VOC LE: 5.7 VOC AP: 5.1**  
**FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: YES**

**738766K™** Acetone, Acrylic polymer, Amorphous silica - precipitated, Butyl acetate, Carbamate resin, Cellulose acetate butyrate, Ethylbenzene(5.7%\*), Hydrotreated heavy naphtha (petroleum), Isobutyl alcohol, Melamine resin, Perylene pigment, Polyester resin, Polyethylene/vinyl acetate, Titanium dioxide(0.3%), Xylene(19%\*)  
**GAL WT: 7.82 WT PCT SOLIDS: 29.55 VOL PCT SOLIDS: 22.96**  
**SOLVENT DENSITY: 7.16 VOC LE: 5.4 VOC AP: 4.9**  
**FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: YES**

**745101K™** Acetone, Acrylic polymer, Butyl acetate, Carbamate resin, Cellulose acetate butyrate, Ethylbenzene(5.6%\*), Hydrotreated heavy naphtha (petroleum), Isobutyl alcohol, Melamine resin, Polyester resin, Polyethylene/vinyl acetate, Titanium dioxide(0.6%), Xylene(20%\*)  
**GAL WT: 7.69 WT PCT SOLIDS: 23.80 VOL PCT SOLIDS: 18.45**  
**SOLVENT DENSITY: 7.20 VOC LE: 5.8 VOC AP: 5.2**  
**FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: YES**

**747402K™** Acetone, Acrylic polymer, Butyl acetate, Cellulose acetate butyrate, Ethylbenzene(6.3%\*), Iron oxide, Polyester resin, Polyethylene/vinyl acetate, Quinacridone pigment, Xylene(24%\*)  
**GAL WT: 7.83 WT PCT SOLIDS: 26.41 VOL PCT SOLIDS: 20.12**  
**SOLVENT DENSITY: 7.22 VOC LE: 5.7 VOC AP: 5.2**  
**FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: YES**

**B8424K™** Acetone, Acrylic polymer, Amorphous silica, Butyl acetate, Cellulose acetate butyrate, Ethylbenzene(4.6%\*), Polyester resin, Polyethylene/vinyl acetate, Titanium dioxide(20.1%), Xylene(18%\*)  
**GAL WT: 9.17 WT PCT SOLIDS: 40.45 VOL PCT SOLIDS: 24.22**  
**SOLVENT DENSITY: 7.19 VOC LE: 5.3 VOC AP: 4.8**  
**FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: YES**

**B8469K™** Acetone, Acrylic polymer, Amorphous silica, Butyl acetate, Cellulose acetate butyrate, Ethylbenzene(4.6%\*), Polyester resin, Polyethylene/vinyl acetate, Titanium dioxide(20.1%), Xylene(18%\*)  
**GAL WT: 9.17 WT PCT SOLIDS: 40.44 VOL PCT SOLIDS: 24.21**  
**SOLVENT DENSITY: 7.19 VOC LE: 5.3 VOC AP: 4.8**  
**FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: YES**

**B8550K™** Acetone, Acrylic polymer, Amorphous silica, Butyl acetate, Cellulose acetate butyrate, Ethylbenzene(4.6%\*), Polyester resin, Polyethylene/vinyl acetate, Titanium dioxide(18.5%), Xylene(18%\*)  
**GAL WT: 9.00 WT PCT SOLIDS: 38.65 VOL PCT SOLIDS: 23.29**  
**SOLVENT DENSITY: 7.18 VOC LE: 5.4 VOC AP: 4.9**  
**FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: YES**

**B8713K™** Acetone, Acrylic polymer, Butyl acetate, Cellulose acetate butyrate, Ethylbenzene(7.3%\*), Pigment red 202, Polyester resin, Polyethylene/vinyl acetate, Xylene(27%\*)  
**GAL WT: 7.80 WT PCT SOLIDS: 27.13 VOL PCT SOLIDS: 21.31**  
**SOLVENT DENSITY: 7.23 VOC LE: 5.6 VOC AP: 5.2**  
**FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: YES**

**B8833K™** Acetone, Acrylic polymer, Amorphous silica, Butyl acetate, Cellulose acetate butyrate, Ethylbenzene(4.6%\*), Polyester resin, Polyethylene/vinyl acetate, Titanium dioxide(20.2%), Xylene(18%\*)  
**GAL WT: 9.18 WT PCT SOLIDS: 40.57 VOL PCT SOLIDS: 24.29**  
**SOLVENT DENSITY: 7.19 VOC LE: 5.3 VOC AP: 4.8**  
**FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: YES**

**B9025K™** Acetone, Acrylic polymer, Butyl acetate, Carbamate resin, Carbon black(0.1%), Cellulose acetate butyrate, Ethylbenzene(5.9%\*), Melamine resin, Phthalocyanine green, Polyester resin, Polyethylene/vinyl acetate, Silica alumina ceramic, Xylene(22%\*)  
**GAL WT: 7.84 WT PCT SOLIDS: 25.74 VOL PCT SOLIDS: 19.16**  
**SOLVENT DENSITY: 7.21 VOC LE: 5.7 VOC AP: 5.2**  
**FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: YES**

**B9031K™** Acetone, Acrylic polymer, Butyl acetate, Cellulose acetate butyrate, Ethylbenzene(6.8%\*), Pigment red 202, Polyester resin, Polyethylene/vinyl acetate, Xylene(26%\*)  
**GAL WT: 7.79 WT PCT SOLIDS: 25.37 VOL PCT SOLIDS: 19.46**  
**SOLVENT DENSITY: 7.23 VOC LE: 5.7 VOC AP: 5.3**  
**FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: YES**

**B9118K™** Acetone, Acrylic polymer, Aluminum hydroxide, Amorphous silica, Butyl acetate, Cellulose acetate butyrate, Ethylbenzene(4.6%\*), Polyester resin, Polyethylene/vinyl acetate, Titanium dioxide(31.1%), Xylene(17%\*)  
**GAL WT: 10.40 WT PCT SOLIDS: 51.86 VOL PCT SOLIDS: 30.66**  
**SOLVENT DENSITY: 7.20 VOC LE: 4.9 VOC AP: 4.6**  
**FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: YES**

**B9145K™** Acetone, Acrylic polymer, Amorphous silica, Butyl acetate, Cellulose acetate butyrate, Ethylbenzene(2.3 - 5.7%\*), Polyester resin, Polyethylene/vinyl acetate, Titanium dioxide(20.0%), Xylene(17 - 20%\*)  
**GAL WT: 9.17 WT PCT SOLIDS: 40.48 VOL PCT SOLIDS: 24.24**  
**SOLVENT DENSITY: 7.19 VOC LE: 5.3 VOC AP: 4.8**  
**FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: YES**

**B9326K™** Acetone, Acrylic polymer, Butyl acetate, C.i. pigment red 254, Cellulose acetate butyrate, Ethylbenzene(7.0%\*), Polyester resin, Polyethylene/vinyl acetate, Xylene(26%\*)

**GAL WT: 7.86 WT PCT SOLIDS: 30.05 VOL PCT SOLIDS: 23.84**  
**SOLVENT DENSITY: 7.23 VOC LE: 5.4 VOC AP: 5.1**  
**FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALY REACTIVE: YES**

**B9444K™** Acetone, Acrylic polymer, Amorphous silica, Butyl acetate, Cellulose acetate butyrate, Ethylbenzene(4.6%\*), Polyester resin, Polyethylene/vinyl acetate, Titanium dioxide(20.3%), Xylene(18%\*)  
**GAL WT: 9.18 WT PCT SOLIDS: 40.63 VOL PCT SOLIDS: 24.32**  
**SOLVENT DENSITY: 7.19 VOC LE: 5.3 VOC AP: 4.8**  
**FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALY REACTIVE: YES**

**D8590K™** Acetone, Acrylic polymer, Aluminum(6%\*), Butyl acetate, Carbamate resin, Cellulose acetate butyrate, Ethylbenzene(5.6%\*), Polyester resin, Polyethylene/vinyl acetate, Silica alumina ceramic, Stoddard solvent, Xylene(20%\*)  
**GAL WT: 7.98 WT PCT SOLIDS: 28.17 VOL PCT SOLIDS: 20.27**  
**SOLVENT DENSITY: 7.20 VOC LE: 5.6 VOC AP: 5.1**  
**FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 1 OSHA STORAGE: IB**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALY REACTIVE: YES**

**F7996K™** Acetone, Acrylic polymer, Butyl acetate, C.i. pigment red 254, Cellulose acetate butyrate, Ethylbenzene(6.7%\*), Mica, Polyester resin, Polyethylene/vinyl acetate, Xylene(25%\*)  
**GAL WT: 7.81 WT PCT SOLIDS: 25.81 VOL PCT SOLIDS: 19.78**  
**SOLVENT DENSITY: 7.24 VOC LE: 5.7 VOC AP: 5.3**  
**FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALY REACTIVE: YES**

**M5150K™** Acetone, Acrylic polymer, Aluminum oxide(1%\*), Butyl acetate, Carbamate resin, Cellulose acetate butyrate, Ethylbenzene(6.0%\*), Isobutyl alcohol, Melamine resin, Polyester resin, Polyethylene/vinyl acetate, Titanium dioxide(0.4%), Xylene(20%\*)  
**GAL WT: 7.75 WT PCT SOLIDS: 26.45 VOL PCT SOLIDS: 20.75**  
**SOLVENT DENSITY: 7.21 VOC LE: 5.6 VOC AP: 5.0**  
**FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALY REACTIVE: YES**

**M8744K™** Acetone, Acrylic polymer, Butyl acetate, Carbamate resin, Cellulose acetate butyrate, Ethylbenzene(6.1%\*), Hydrotreated heavy naphtha (petroleum), Isobutyl alcohol, Melamine resin, Polyester resin, Polyethylene/vinyl acetate, Titanium dioxide(0.2%), Xylene(20%\*)  
**GAL WT: 7.71 WT PCT SOLIDS: 26.49 VOL PCT SOLIDS: 21.08**  
**SOLVENT DENSITY: 7.19 VOC LE: 5.6 VOC AP: 5.0**  
**FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALY REACTIVE: YES**

**M8757K™** Acetone, Acrylic polymer, Butyl acetate, Carbamate resin, Carbon black(0.1%), Cellulose acetate butyrate, Ethylbenzene(5.7%\*), Melamine resin, Perylene maroon, Polyester resin, Polyethylene/vinyl acetate, Xylene(21%\*)  
**GAL WT: 8.00 WT PCT SOLIDS: 31.90 VOL PCT SOLIDS: 24.53**  
**SOLVENT DENSITY: 7.23 VOC LE: 5.3 VOC AP: 4.9**  
**FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALY REACTIVE: YES**

**M9318K™** Acetone, Acrylic polymer, Aluminum(2%\*), Aluminum oxide(2%\*), Butyl acetate, Carbamate resin, Carbon black(0.1%), Cellulose acetate butyrate, Ethylbenzene(5.1%\*), Isobutyl alcohol, Melamine resin, Polyester resin, Polyethylene/vinyl acetate, Titanium dioxide(1.2%), Xylene(19%\*)  
**GAL WT: 7.86 WT PCT SOLIDS: 25.89 VOL PCT SOLIDS: 18.89**  
**SOLVENT DENSITY: 7.21 VOC LE: 5.7 VOC AP: 5.1**  
**FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALY REACTIVE: YES**

**M9369K™** Acetone, Acrylic polymer, Aluminum oxide(1%\*), Butyl acetate, Carbamate resin, Cellulose acetate butyrate, Ethylbenzene(6.0%\*),

Hydrotreated heavy naphtha (petroleum), Isobutyl alcohol, Melamine resin, Polyester resin, Polyethylene/vinyl acetate, Titanium dioxide(0.4%), Xylene(20%\*)

**GAL WT: 7.75 WT PCT SOLIDS: 26.69 VOL PCT SOLIDS: 20.94**  
**SOLVENT DENSITY: 7.20 VOC LE: 5.6 VOC AP: 5.0**  
**FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALY REACTIVE: YES**

**P0931K™** Acetone, Acrylic polymer, Butyl acetate, Carbamate resin, Carbon black(0.4%), Cellulose acetate butyrate, Ethylbenzene(5.7%\*), Isobutyl alcohol, Melamine resin, Polyester resin, Polyethylene/vinyl acetate, Xylene(20%\*)  
**GAL WT: 7.72 WT PCT SOLIDS: 25.16 VOL PCT SOLIDS: 19.63**  
**SOLVENT DENSITY: 7.20 VOC LE: 5.7 VOC AP: 5.1**  
**FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALY REACTIVE: YES**

**P0932K™** Acetone, Acrylic polymer, Aluminum(1%\*), Butyl acetate, Carbamate resin, Carbon black(0.3%), Cellulose acetate butyrate, Ethylbenzene(5.5%\*), Melamine resin, Perylene maroon, Polyester resin, Polyethylene/vinyl acetate, Titanium dioxide(0.3%), Xylene(20%\*)  
**GAL WT: 7.80 WT PCT SOLIDS: 25.90 VOL PCT SOLIDS: 19.80**  
**SOLVENT DENSITY: 7.22 VOC LE: 5.7 VOC AP: 5.1**  
**FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALY REACTIVE: YES**

**P0960K™** Acetone, Acrylic polymer, Butyl acetate, Carbamate resin, Carbon black(0.6%), Cellulose acetate butyrate, Ethylbenzene(5.5%\*), Isobutyl alcohol, Melamine resin, Polyester resin, Polyethylene/vinyl acetate, Titanium dioxide(0.2%), Xylene(19%\*)  
**GAL WT: 7.69 WT PCT SOLIDS: 24.55 VOL PCT SOLIDS: 19.25**  
**SOLVENT DENSITY: 7.20 VOC LE: 5.7 VOC AP: 5.1**  
**FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALY REACTIVE: YES**

**P2236K™** Acetone, Acrylic polymer, Butyl acetate, Carbamate resin, Cellulose acetate butyrate, Ethylbenzene(5.3%\*), Isobutyl alcohol, Melamine resin, Polyester resin, Polyethylene/vinyl acetate, Xylene(20%\*)  
**GAL WT: 7.65 WT PCT SOLIDS: 22.06 VOL PCT SOLIDS: 17.06**  
**SOLVENT DENSITY: 7.20 VOC LE: 5.9 VOC AP: 5.2**  
**FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALY REACTIVE: YES**

**P4040K™** Acetone, Acrylic polymer, Butyl acetate, Carbamate resin, Carbon black(0.3%), Cellulose acetate butyrate, Ethylbenzene(5.5%\*), Hydrotreated heavy naphtha (petroleum), Isobutyl alcohol, Melamine resin, Polyester resin, Polyethylene/vinyl acetate, Xylene(19%\*)  
**GAL WT: 7.67 WT PCT SOLIDS: 23.93 VOL PCT SOLIDS: 18.74**  
**SOLVENT DENSITY: 7.19 VOC LE: 5.7 VOC AP: 5.1**  
**FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALY REACTIVE: YES**

**P4577K™** Acetone, Acrylic polymer, Butyl acetate, Carbamate resin, Cellulose acetate butyrate, Ethylbenzene(6.1%\*), Isobutyl alcohol, Melamine resin, Polyester resin, Polyethylene/vinyl acetate, Titanium dioxide(0.2%), Xylene(21%\*)  
**GAL WT: 7.66 WT PCT SOLIDS: 24.84 VOL PCT SOLIDS: 19.96**  
**SOLVENT DENSITY: 7.20 VOC LE: 5.7 VOC AP: 5.1**  
**FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALY REACTIVE: YES**

**P4846K™** Acetone, Acrylic polymer, Butyl acetate, Carbamate resin, Cellulose acetate butyrate, Ethylbenzene(6.1%\*), Isobutyl alcohol, Melamine resin, Polyester resin, Polyethylene/vinyl acetate, Titanium dioxide(0.3%), Xylene(20%\*)  
**GAL WT: 7.69 WT PCT SOLIDS: 25.92 VOL PCT SOLIDS: 20.70**  
**SOLVENT DENSITY: 7.20 VOC LE: 5.6 VOC AP: 5.0**  
**FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB**

**TSCA STATUS: In Compliance PHOTO-CHEMICALY REACTIVE: YES**

**P4927K™** Acetone, Acrylic polymer, Butyl acetate, Carbamate resin, Carbon black(0.3%), Cellulose acetate butyrate, Ethylbenzene(5.6%\*), Hydrotreated heavy naphtha (petroleum), Isobutyl alcohol, Melamine resin, Polyester resin, Polyethylene/vinyl acetate, Titanium dioxide(0.3%), Xylene(20%\*)

**GAL WT: 7.68 WT PCT SOLIDS: 24.18 VOL PCT SOLIDS: 18.93**  
**SOLVENT DENSITY: 7.19 VOC LE: 5.7 VOC AP: 5.1**

**FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALY REACTIVE: YES**

**P6640K™** Acetone, Acrylic polymer, Butyl acetate, Carbamate resin, Cellulose acetate butyrate, Ethylbenzene(5.6%\*), Isobutyl alcohol, Melamine resin, Polyester resin, Polyethylene/vinyl acetate, Titanium dioxide(0.1%), Xylene(18%\*)

**GAL WT: 7.68 WT PCT SOLIDS: 26.71 VOL PCT SOLIDS: 21.63**  
**SOLVENT DENSITY: 7.19 VOC LE: 5.5 VOC AP: 4.9**

**FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALY REACTIVE: YES**

**P6647K™** Acetone, Acrylic polymer, Butyl acetate, Cellulose acetate butyrate, Ethylbenzene(6.3%\*), Hydrotreated heavy naphtha (petroleum), Isobutyl alcohol, Perylene maroon, Polyester resin, Polyethylene/vinyl acetate, Titanium dioxide(0.1%), Xylene(22%\*)

**GAL WT: 7.88 WT PCT SOLIDS: 29.75 VOL PCT SOLIDS: 22.99**  
**SOLVENT DENSITY: 7.20 VOC LE: 5.4 VOC AP: 5.0**

**FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALY REACTIVE: YES**

**P6755K™** Acetone, Acrylic polymer, Aluminum oxide(1%\*), Butyl acetate, Carbamate resin, Cellulose acetate butyrate, Ethylbenzene(5.3%\*), Isobutyl alcohol, Melamine resin, Polyester resin, Polyethylene/vinyl acetate, Titanium dioxide(1.4%), Xylene(20%\*)

**GAL WT: 7.78 WT PCT SOLIDS: 25.11 VOL PCT SOLIDS: 18.92**  
**SOLVENT DENSITY: 7.21 VOC LE: 5.7 VOC AP: 5.1**

**FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALY REACTIVE: YES**

**P6834K™** Acetone, Acrylic polymer, Butyl acetate, Carbamate resin, Cellulose acetate butyrate, Ethylbenzene(5.1%\*), Isobutyl alcohol, Melamine resin, Polyester resin, Polyethylene/vinyl acetate, Titanium dioxide(2.9%), Xylene(18%\*)

**GAL WT: 7.92 WT PCT SOLIDS: 27.98 VOL PCT SOLIDS: 20.58**  
**SOLVENT DENSITY: 7.20 VOC LE: 5.6 VOC AP: 5.0**

**FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALY REACTIVE: YES**

**P7105K™** Acetone, Acrylic polymer, Amorphous silica - precipitated, Butyl acetate, Carbamate resin, Cellulose acetate butyrate, Ethylbenzene(6.0%\*), Hydrotreated heavy naphtha (petroleum), Isobutyl alcohol, Polyester resin, Polyethylene/vinyl acetate, Titanium dioxide(0.4%), Xylene(19%\*)

**GAL WT: 7.74 WT PCT SOLIDS: 27.49 VOL PCT SOLIDS: 21.77**  
**SOLVENT DENSITY: 7.19 VOC LE: 5.5 VOC AP: 5.0**

**FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALY REACTIVE: YES**

**P7304K™** Acetone, Acrylic polymer, Butyl acetate, Carbamate resin, Cellulose acetate butyrate, Ethylbenzene(5.3%\*), Hydrotreated heavy naphtha (petroleum), Isobutyl alcohol, Melamine resin, Polyester resin, Polyethylene/vinyl acetate, Xylene(19%\*)

**GAL WT: 7.67 WT PCT SOLIDS: 24.11 VOL PCT SOLIDS: 18.86**  
**SOLVENT DENSITY: 7.18 VOC LE: 5.7 VOC AP: 5.1**

**FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALY REACTIVE: YES**

**P7333K™** Acetone, Acrylic polymer, Aluminum oxide(1%\*), Butyl acetate, Carbamate resin, Carbon black(0.1%), Cellulose acetate butyrate,

Ethylbenzene(5.7%\*), Isobutyl alcohol, Melamine resin, Polyester resin, Polyethylene/vinyl acetate, Titanium dioxide(0.7%), Xylene(22%\*)

**GAL WT: 7.74 WT PCT SOLIDS: 24.06 VOL PCT SOLIDS: 18.31**  
**SOLVENT DENSITY: 7.21 VOC LE: 5.8 VOC AP: 5.2**

**FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALY REACTIVE: YES**

**W8430K™** Acetone, Acrylic polymer, Amorphous silica, Butyl acetate, Cellulose acetate butyrate, Ethylbenzene(4.6%\*), Polyester resin, Polyethylene/vinyl acetate, Titanium dioxide(20.2%), Xylene(18%\*)

**GAL WT: 9.18 WT PCT SOLIDS: 40.67 VOL PCT SOLIDS: 24.36**  
**SOLVENT DENSITY: 7.18 VOC LE: 5.3 VOC AP: 4.8**

**FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALY REACTIVE: YES**

**Footnotes:**

**TSCA: in compliance** = In compliance with TSCA Inventory requirements for commercial purposes.

**ACGIH** = American Conference of Governmental Industrial Hygienists.

**IARC** = International Agency for Research on Cancer.

**NTP** = National Toxicology Program.

**OSHA** = Occupational Safety and Health Administration.

**PNOR** = Particles not otherwise regulated.

**PNOC** = Particles not otherwise classified.

**STEL** = Short term exposure limit.

**TWA** = Time-weighted average.

**TM** = Is a Trademark of E.I. DuPont de Nemours Co.

\* = Section 313 Supplier Notification: These chemicals are subject to the reporting requirements of Section 313 of the Emergency planning and Right-to-Know act of 1986 and of 40 CFR 372.

@ = Listed as a Clean Air Act Hazardous Air Pollutant.

# = EPCRA Section 302 - Extremely hazardous substances.

**Notice:**

The information on this Material Safety Data Sheet relates only to the specific material designated herein and does not relate to use in combination with any other material or in any process.

Product Manager: Refinish Sales

Prepared by: Y. B. Yarbrough