

**SECTION 1. Identification of the substance/preparation and of the company/undertaking**

Manufacturer: E.I. du Pont de Nemours & Co.  
DuPont Performance Coatings  
Wilmington, DE, 19898

Telephone: Product information: (800) 441-7515  
Medical emergency: (800) 441-3637  
Transportation emergency: (800) 424-9300  
(CHEMTREC)

Product: **Cromax® Pro**

DOT Shipping Name: See DOT Addendum.

Hazardous Materials Information: See Section 10.

Copyright 2007 E. I. duPont de Nemours and Company. All rights reserved. Copies may be made only for those using DuPont products.

**SECTION 2. Composition/information on ingredients**

INGREDIENTS	CAS #	VAPOR PRESSURE	EXPOSURE LIMITS
2-amino-2-methyl-1-propanol	124-68-5	<0.3	D 500.0 ppm 8 & 12 hour TWA A None O None
Acetone	67-64-1	247.0@68.0°F	A 750.0 ppm 15 min STEL A 500.0 ppm O 1000.0 ppm D 500.0 ppm 8 & 12 hour TWA
Acrylic polymer-A	NotAvail	None	A None O None
Acrylic polymer-B	70587-60-9	None	A None O None
Acrylic resin	NotAvail	None	A None O None
Acrylic resin (ts)	NotAvail	None	A None O None
Acrylic resin - waterborne	NotAvail	None	A None O None
Aluminum	7429-90-5	None	A 10.0 mg/m3 particulate A 5.0 mg/m3 Dust O 15.0 mg/m3 Total Dust O 5.0 mg/m3 Respirable Dust
Aluminum hydroxide	21645-51-2	None	A None O None

INGREDIENTS	CAS #	VAPOR PRESSURE	EXPOSURE LIMITS
Aluminum oxide	1344-28-1	None	A 10.0 mg/m3 O 15.0 mg/m3 Total Dust O 5.0 mg/m3 Respirable Dust
Amorphous silica	7631-86-9	None	A 10.0 mg/m3 Total Dust O 20.0 mppcf D 3.0 mg/m3
Anthraquinone pigment	NotAvail	None	A None O None
C.i. pigment red 254	84632-65-5	None	A None O None
C.i. pigment violet 23	6358-30-1	None	A None O None
Carbon black	1333-86-4	None	A 3.5 mg/m3 O 3.5 mg/m3 D 0.5 mg/m3 8 & 12 hour TWA
Copper phthalocyanine	147-14-8	None	A None O None
Dipropylene glycol methyl ether	34590-94-8	0.4@25.0°C	A 150.0 ppm 15 min STEL Skin A 100.0 ppm Skin O 600.0 mg/m3 PEL Skin O 100.0 ppm Skin
Dispersing agent	NotAvail	<0.0	A None O None
Ethylene glycol monobutyl ether	111-76-2	0.6	A 20.0 ppm O 50.0 ppm Skin D 5.0 ppm Skin D 5.0 ppm
Hydrotreated heavy naphtha (petroleum)	64742-48-9	0.7@68.0°F	A 100.0 ppm O 500.0 ppm D 100.0 ppm
Iron hydroxide	20344-49-4	None	A None O None
Iron oxide-A	1309-37-1	None	A 5.0 mg/m3 Respirable Dust O 10.0 mg/m3 D 3.0 mg/m3
Iron oxide-B	1309-37-1	None	A None

INGREDIENTS	CAS #	VAPOR PRESSURE	EXPOSURE LIMITS	INGREDIENTS	CAS #	VAPOR PRESSURE	EXPOSURE LIMITS
Isoindolinone pigment	36888-99-0	None	O None A None O None				O 5.0 mg/m3 TWA Respirable Dust PNOR
Isopropyl alcohol	67-63-0	48.0	A 400.0 ppm 15 min STEL A 200.0 ppm O 400.0 ppm D 200.0 ppm 8 & 12 hour TWA	Phthalocyanine green	1328-53-6	None	A 3.0 mg/m3 TWA Respirable Dust A 10.0 mg/m3 TWA inhalable dust O 15.0 mg/m3 TWA Total Dust O 5.0 mg/m3 TWA Respirable Dust
Light yellow lemon yellow oxide pigment	51274-00-1	None	A None O None				
Medium mineral spirits	64742-88-7	0.3@68.0°F	D 50.0 ppm 8 & 12 hour TWA A None O None	Phthalocyanine green pigment	14302-13-7	None	A None O None
Melamine resin	108-78-1	67.0@315.0°C	A None O None	Pigment red 202	3089-17-6	None	A 3.0 mg/m3 Respirable Dust A 10.0 mg/m3 inhalable dust PNOR O 5.0 mg/m3 Respirable Dust PNOR O 15.0 mg/m3
Mica	12001-26-2	None	A 3.0 mg/m3 Respirable Dust O 20.0 mppcf O 3.0 mg/m3 Respirable Dust				
Monoazo pigment	12236-62-3	None	A 10.0 mg/m3 inhalable dust particulate O 15.0 mg/m3 Total Dust O 5.0 mg/m3 Respirable Dust	Polypropylene glycol	25322-69-4	<0.0	A None O None
N-pentanol	71-41-0	1.5	A None O None	Polyurethane resin	NotAvail	None	A None O None
N-propanol	71-23-8	19.0	A 100.0 ppm O 250.0 ppm 15 min STEL O 200.0 ppm Skin D 200.0 ppm	Proprietary copper compound	NotAvail	None	A None O None
Nickel azo complex (py 150)	68511-62-6	None	A None O None	Propylene glycol methyl ether	107-98-2	11.2@77.0°F	A 150.0 ppm 15 min STEL A 100.0 ppm O None
Perylene pigment	5521-31-3	None	A 10.0 mg/m3 O None	Quinacridone pigment	1047-16-1	None	A 10.0 mg/m3 inhalable dust A 3.0 mg/m3 O 15.0 mg/m3 Total Dust PNOR O 5.0 mg/m3 Respirable Dust D 10.0 mg/m3 Total Dust
Phthalocyanine blue pigment	147-14-8	None	A 10.0 mg/m3 inhalable dust PNOC A 3.0 mg/m3 respirable particulate PNOC O 15.0 mg/m3 Total Dust PNOR	Quinophthalone yellow pigment	30125-47-4	None	A None O None
				Rheology agent	NotAvail	18.0	A None O None
				Synthetic magnesium silicate	53320-86-8	None	S 15.0 mg/m3 TWA

INGREDIENTS	CAS #	VAPOR PRESSURE	EXPOSURE LIMITS
Tetrachloroisosolinone yellow pigment	5590-18-1	None	PNOR Total Dust S 5.0 mg/m3 TWA PNOR Respirable Dust A None O None
Titanium dioxide	13463-67-7	None	A 10.0 mg/m3 O None A 10.0 mg/m3 O 15.0 mg/m3 Total Dust D 10.0 mg/m3 Total Dust D 5.0 mg/m3 Respirable Dust
Titanium dioxide (rutile)	1317-80-2	None	A 10.0 mg/m3 TWA Total Dust O 10.0 mg/m3 Total Dust O 5.0 mg/m3 Respirable Dust D 10.0 mg/m3 Total Dust D 5.0 mg/m3 Respirable Dust
Titanium dioxide, anatase	1317-70-0	None	A None O None
Urea-formaldehyde condensation polymer	9011-05-6	None	A None O None
Water	7732-18-5	23.6	A None O None
Yellow pigment	Not Avail	None	A None O None

\*A=ACGIH, O=OSHA, D=DuPont, S=Suppliers. Limits are 8 hour TWA unless otherwise specified. Vapor pressure @ 20° C unless otherwise noted.

**SECTION 3. Hazards identification**

**Potential Health Effects:**

**Inhalation:**

May cause nose and throat irritation. May cause nervous system depression characterized by the following progressive steps: headache, dizziness, nausea, staggering gait, confusion, unconsciousness. Reports have associated repeated and prolonged overexposure to solvents with permanent brain and nervous system damage.

**Ingestion:**

May result in gastrointestinal distress.

**Skin or eye contact:**

May cause irritation or burning of the eyes. Repeated or prolonged liquid contact may cause skin irritation with discomfort and dermatitis.

**Other Potential Health Effects in addition to those listed above:**

**2-amino-2-methyl-1-propanol**

Eye burns. Ingestion may cause any of the following: burns to mouth and stomach, gastrointestinal irritation, aspiration leading to lung damage..

**Acetone**

The following medical conditions may be aggravated by exposure: lung disease, eye disorders, skin disorders. Overexposure may cause damage to any of the following organs/systems: blood, central nervous system, eyes, kidneys, liver, respiratory system, skin.

**Acrylic polymer-A**

Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of the following: skin.

**Acrylic resin (ts)**

Skin or eye contact may cause any of the following: irritation.

**Carbon black**

Is an IARC, NTP or OSHA carcinogen. Has shown carcinogenic activity in laboratory animals at high doses. Significance to man is unknown. The following medical conditions may be aggravated by exposure: asthma, respiratory disease.

WARNING: This chemical is known to the State of California to cause cancer.

**Ethylene glycol monobutyl ether**

Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of the following: bone marrow, central nervous system, eyes, gastrointestinal system, kidneys, liver, respiratory system, skin. May cause injury to the kidneys, liver, blood and/or bone marrow. Repeated overexposure may result in damage to the blood. Eye contact may cause corneal injury. Has been toxic to the fetus in laboratory animals at doses that are toxic to the mother. If absorbed through the skin, may be: harmful.

**Hydrotreated heavy naphtha (petroleum)**

Laboratory studies with rats have shown that petroleum distillates can cause kidney damage and kidney or liver tumors. These effects were not seen in similar studies with guinea pigs, dogs, or monkeys. Several studies evaluating petroleum workers have not shown a significant increase of kidney damage or an increase in kidney or liver tumors.

**Isopropyl alcohol**

The following medical conditions may be aggravated by exposure: dermatitis, respiratory disease. Developmental toxicity was seen in rat's offspring at doses that were maternally toxic. Contact will cause moderate to severe redness and swelling, itching, tingling sensation, painful burning. May cause injury to the cornea of the eyes. Prolonged or repeated exposure may cause damage to any of the following organs/systems: liver. Ingestion studies on laboratory animals showed that very high oral doses caused increased liver and kidney weights.

**Light yellow lemon yellow oxide pigment**

Contact may cause skin irritation with discomfort or rash. May cause eye irritation with discomfort, tearing, or blurred vision.

**Medium mineral spirits**

Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of the following: central nervous system, kidneys, liver, respiratory system, skin. This substance may cause damage to any of the following organs/systems: blood, central nervous system, eyes, kidneys, liver, lungs, reproductive system, skin. Laboratory studies with rats have shown that petroleum distillates can cause kidney damage and kidney or liver tumors. These effects were not seen in similar studies with guinea pigs, dogs, or monkeys. Several studies evaluating petroleum workers have not shown a significant increase of kidney damage or an increase in kidney or liver tumors.

**Melamine resin**

This chemical is a formaldehyde donor. Formaldehyde is an IARC, NTP or OSHA carcinogen and has shown mutagenic activity in laboratory cell

culture tests. May induce pulmonary sensitization or significant irritation of the respiratory airways. Formaldehyde has produced tumors in the nasal passages of laboratory animals when exposed to high concentrations for a two year period. IARC has concluded epidemiology studies found evidence of formaldehyde related nasopharyngeal cancer in humans and have classified formaldehyde as a confirmed human carcinogen. DuPont toxicologists have reviewed these studies and classified formaldehyde as a possible human carcinogen.

#### Mica

Repeated or prolonged inhalation may cause any of the following: lung irritation. Long-term respiratory exposure exceeding TLV may damage the lungs, leading to bronchitis and impairment of lung capacity.

#### N-propanol

Has shown mutagenic activity in laboratory cell culture tests. Has shown carcinogenic activity in laboratory animals at high doses. Significance to man is unknown. May cause abnormal liver function. Can be absorbed through the skin in harmful amounts.

#### Nickel azo complex (py 150)

WARNING: This chemical is known to the State of California to cause cancer.

#### Propylene glycol methyl ether

Tests in laboratory animals have shown effects on any of the following organs/systems: kidneys, liver. Aspiration may occur during swallowing or vomiting, resulting in lung damage.

#### Titanium dioxide

Is an IARC, NTP or OSHA carcinogen. In a lifetime inhalation test, lung cancers were found in some rats exposed to 250 mg/m<sup>3</sup> respirable titanium dust. Analysis of the titanium dioxide concentrations in the rat's lungs showed that the lung clearance mechanism was overwhelmed and that the results at the massive 250 mg/m<sup>3</sup> level are not relevant to the workplace. Results of a DuPont epidemiology study showed that employees who had been exposed to Titanium Dioxide were at no greater risk of developing lung cancer than were employees who had not been exposed to Titanium dioxide. No pulmonary fibrosis was found in any of the employees and no association was observed between Titanium dioxide exposure and chronic respiratory disease or x-ray abnormalities. Based on the results of this study DuPont concludes that titanium dioxide will not cause lung cancer or chronic respiratory disease in humans at concentrations experienced in the workplace.

#### Titanium dioxide (rutile)

Is an IARC, NTP or OSHA carcinogen. In a lifetime inhalation test, lung cancers were found in some rats exposed to 250 mg/m<sup>3</sup> respirable titanium dust. Analysis of the titanium dioxide concentrations in the rat's lungs showed that the lung clearance mechanism was overwhelmed and that the results at the massive 250 mg/m<sup>3</sup> level are not relevant to the workplace. Results of a DuPont epidemiology study showed that employees who had been exposed to Titanium Dioxide were at no greater risk of developing lung cancer than were employees who had not been exposed to Titanium dioxide. No pulmonary fibrosis was found in any of the employees and no association was observed between Titanium dioxide exposure and chronic respiratory disease or x-ray abnormalities. Based on the results of this study DuPont concludes that titanium dioxide will not cause lung cancer or chronic respiratory disease in humans at concentrations experienced in the workplace.

#### Titanium dioxide, anatase

Is an IARC, NTP or OSHA carcinogen. In a lifetime inhalation test, lung cancers were found in some rats exposed to 250 mg/m<sup>3</sup> respirable titanium dust. Analysis of the titanium dioxide concentrations in the rat's lungs showed that the lung clearance mechanism was overwhelmed and that the results at the massive 250 mg/m<sup>3</sup> level are not relevant to the workplace. Results of a DuPont epidemiology study showed that employees who had been exposed to Titanium Dioxide were at no greater risk of developing lung cancer than were employees who had not been exposed to Titanium dioxide. No pulmonary fibrosis was found in any of the employees and no association was observed between Titanium dioxide

exposure and chronic respiratory disease or x-ray abnormalities. Based on the results of this study DuPont concludes that titanium dioxide will not cause lung cancer or chronic respiratory disease in humans at concentrations experienced in the workplace.

#### Urea-formaldehyde condensation polymer

This chemical is a formaldehyde donor. Formaldehyde is an IARC, NTP or OSHA carcinogen and has shown mutagenic activity in laboratory cell culture tests. May induce pulmonary sensitization or significant irritation of the respiratory airways. Formaldehyde has produced tumors in the nasal passages of laboratory animals when exposed to high concentrations for a two year period. IARC has concluded epidemiology studies found evidence of formaldehyde related nasopharyngeal cancer in humans and have classified formaldehyde as a confirmed human carcinogen. DuPont toxicologists have reviewed these studies and classified formaldehyde as a possible human carcinogen.

### SECTION 4. First aid measures

#### First Aid Procedures:

##### Inhalation:

If affected by inhalation of vapor or spray mist, move to fresh air. If not breathing, give artificial respiration, preferably mouth-to-mouth. If breathing difficulty persists, or occurs later, consult a physician.

##### Ingestion:

In the unlikely event of ingestion, DO NOT INDUCE VOMITING. Call a physician immediately and have names of ingredients available.

##### Skin or eye contact:

In case of eye contact, immediately flush with plenty of water for at least 15 minutes; call a physician. In case of skin contact, wash thoroughly with soap and water. If irritation occurs, contact a physician.

### SECTION 5. Fire-fighting measures

**Flash Point (Closed Cup):** See Section 11 for exact values.

**Flammable Limits:** LFL 0 % UFL 13.7 %

#### Extinguishing Media:

Universal aqueous film-forming foam, carbon dioxide, dry chemical.

#### Fire Fighting Procedures:

Full protective equipment, including self-contained breathing apparatus, is recommended. Water from fog nozzles may be used to prevent pressure build-up.

#### Fire and Explosion Hazards:

For flammable liquids, vapor/air will ignite when an ignition source is present. In other cases, when heated above the flash point, emits flammable vapors which, when mixed with air, can burn or be explosive. Fine mists or sprays may be flammable at temperatures below the flash point.

### SECTION 6. Accidental release measures

#### Procedures for cleaning up spills or leaks:

Ventilate area. Remove sources of ignition. Prevent skin and eye contact and breathing of vapor. If material does not contain or is not mixed with an isocyanate activator/hardener: Wear a properly fitted air-purifying

respirator with organic vapor cartridges (NIOSH approved TC-23C), eye protection, gloves and protective clothing. Confine, remove with inert absorbent, and dispose of properly.

**Ecological information:**

There is no data available on the product. The product should not be allowed to enter drains, water courses or the soil.

**SECTION 7. Handling and storage**

**Precautions to be taken in handling and storing:**

Observe label precautions. If combustible (flashpoint between 100 - 200 deg F), keep away from heat, sparks and flame. If flammable (flashpoint less than 100 deg F), also keep away from static discharges and other sources of ignition. If material is extremely flammable (flashpoint less than 20 deg F) or flammable, VAPORS MAY IGNITE EXPLOSIVELY OR CAUSE FLASH FIRE, respectively. Vapors may spread long distances. Prevent buildup of vapors. Close container after each use. Ground containers when pouring. Wash thoroughly after handling and before eating or smoking. Do not store above 120 deg F. If product is waterbased, do not freeze.

**Other precautions:**

If material is a coating: do not sand, flame cut, braze or weld dry coating without a NIOSH approved air purifying respirator with particulate filters or appropriate ventilation, and gloves.

**SECTION 8. Exposure controls / personal protection**

**Engineering controls and work practices:**

**Ventilation:**

Provide sufficient ventilation in volume and pattern to keep contaminants below applicable exposure limits.

**Respiratory protection:**

Do not breathe vapors or mists. Wear a properly fitted air-purifying respirator with organic vapor cartridges (NIOSH approved TC-23C) and particulate filter (NIOSH TC-84A) during application and until all vapors and spray mists are exhausted. In confined spaces, or in situations where continuous spray operations are typical, or if proper air-purifying respirator fit is not possible, wear a positive pressure, supplied-air respirator (NIOSH TC-19C). In all cases, follow respirator manufacturer's directions for respirator use. Do not permit anyone without protection in the painting area.

**Protective equipment:**

Personal protective equipment should be worn to prevent contact with eyes, skin or clothing.

**Skin protection:**

Neoprene gloves and coveralls are recommended.

**Eye protection:**

Desirable in all industrial situations. Goggles are preferred to prevent eye irritation. If safety glasses are substituted, include splash guard or side shields.

**SECTION 9. Physical and chemical properties**

Evaporation rate	Slower than Ether
Water solubility	NIL
Vapour density	Heavier than air
Approx. Boiling Range ( °C)	82 - 139 °C
Approx. Freezing Range ( °C)	-127 - -95°C
Gallon Weight (lbs/gal)	8.4 - 13.43
Specific Gravity	1.01 - 1.61
Percent Volatile By Volume	70.07 - 95.31
Percent Volatile By Weight	43.40 - 93.92
Percent Solids By Volume	4.69 - 29.93
Percent Solids By Weight	6.08 - 56.60

**SECTION 10. Stability and reactivity**

**Stability:**

Stable

**Incompatibility (materials to avoid):**

None reasonably foreseeable

**Hazardous decomposition products:**

CO, CO2, smoke, and oxides of any heavy metals that are reported in "Composition, Information on Ingredients" section.

**Hazardous Polymerization:**

Will not occur.

**Sensitivity to Static Discharge:**

For flammable materials (flashpoint less than 100 deg F) and combustibles (flashpoint between 100-200 deg F) if heated above the flashpoint, solvent vapors in air may explode if static grounding and bonding is not used during transfer of this product.

**Sensitivity to Mechanical Impact:**

None known.

**SECTION 11. Additional Information**

**WB01™** Acrylic polymer-B, Acrylic resin (ts), Aluminum hydroxide, Amorphous silica, Dipropylene glycol methyl ether, Polyurethane resin, Titanium dioxide(47.3%), Water

**GAL WT: 13.43 WT PCT SOLIDS: 56.60 VOL PCT SOLIDS: 29.38**  
**SOLVENT DENSITY: 8.22 VOC LE: 1.6 VOC AP: 0.6**  
**FLASH POINT: 141°F - 200°F H: 1 F: 2 R: 0 OSHA STORAGE: IIIA**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

**WB02™** Acrylic resin - waterborne, N-pentanol, Polyurethane resin, Titanium dioxide(6.3%), Water

**GAL WT: 8.83 WT PCT SOLIDS: 20.00 VOL PCT SOLIDS: 14.47**  
**SOLVENT DENSITY: 8.21 VOC LE: 2.1 VOC AP: 0.4**  
**FLASH POINT: 141°F - 200°F H: 1 F: 2 R: 0 OSHA STORAGE: IIIA**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

**WB03™** Acrylic polymer-B, Acrylic resin (ts), Aluminum hydroxide, Dipropylene glycol methyl ether, Isopropyl alcohol, Titanium dioxide(17.9%), Water

**GAL WT: 9.66 WT PCT SOLIDS: 25.06 VOL PCT SOLIDS: 12.26**  
**SOLVENT DENSITY: 8.24 VOC LE: 3.6 VOC AP: 0.8**  
**FLASH POINT: 141°F - 200°F H: 1 F: 2 R: 0 OSHA STORAGE: IIIA**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

**WB06™** Carbon black(1.8%), Dispersing agent, Water

**GAL WT: 8.44 WT PCT SOLIDS: 6.08 VOL PCT SOLIDS: 4.69**

**SOLVENT DENSITY: 8.31 VOC LE: 1.4 VOC AP: 0.1**  
**FLASH POINT: 141°F - 200°F H: 0 F: 2 R: 0 OSHA STORAGE: IIIA**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

**WB07™** Acrylic resin - waterborne, Carbon black(0.6%), N-pentanol, Polyurethane resin, Water  
**GAL WT: 8.40 WT PCT SOLIDS: 11.10 VOL PCT SOLIDS: 9.80**  
**SOLVENT DENSITY: 8.24 VOC LE: 2.2 VOC AP: 0.3**  
**FLASH POINT: 141°F - 200°F H: 0 F: 2 R: 0 OSHA STORAGE: IIIA**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

**WB1001™** Acrylic resin - waterborne, Mica, N-pentanol, N-propanol, Polyurethane resin, Propylene glycol methyl ether, Titanium dioxide (rutile)(2.3%), Water  
**GAL WT: 8.80 WT PCT SOLIDS: 25.59 VOL PCT SOLIDS: 19.64**  
**SOLVENT DENSITY: 8.15 VOC LE: 3.0 VOC AP: 1.1**  
**FLASH POINT: 100°F - 141°F H: 2 F: 2 R: 0 OSHA STORAGE: II**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

**WB1002™** Acrylic resin - waterborne, Mica, N-pentanol, N-propanol, Polyurethane resin, Propylene glycol methyl ether, Titanium dioxide (rutile)(3.3%), Water  
**GAL WT: 8.81 WT PCT SOLIDS: 25.59 VOL PCT SOLIDS: 19.49**  
**SOLVENT DENSITY: 8.06 VOC LE: 3.1 VOC AP: 1.1**  
**FLASH POINT: 100°F - 141°F H: 1 F: 2 R: 0 OSHA STORAGE: II**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

**WB1003™** Acrylic resin - waterborne, Mica, N-pentanol, N-propanol, Polyurethane resin, Propylene glycol methyl ether, Titanium dioxide(3.8%), Water  
**GAL WT: 8.82 WT PCT SOLIDS: 25.59 VOL PCT SOLIDS: 19.42**  
**SOLVENT DENSITY: 8.14 VOC LE: 3.1 VOC AP: 1.1**  
**FLASH POINT: 100°F - 141°F H: 1 F: 2 R: 0 OSHA STORAGE: II**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

**WB1004™** Acrylic resin - waterborne, Mica, N-pentanol, N-propanol, Polyurethane resin, Propylene glycol methyl ether, Titanium dioxide (rutile)(5.8%), Water  
**GAL WT: 8.83 WT PCT SOLIDS: 25.59 VOL PCT SOLIDS: 19.35**  
**SOLVENT DENSITY: 8.06 VOC LE: 3.1 VOC AP: 1.1**  
**FLASH POINT: 100°F - 141°F H: 1 F: 2 R: 0 OSHA STORAGE: II**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

**WB1005™** Acrylic resin - waterborne, Mica, N-pentanol, N-propanol, Polyurethane resin, Propylene glycol methyl ether, Titanium dioxide (rutile)(4.0%), Water  
**GAL WT: 8.82 WT PCT SOLIDS: 25.59 VOL PCT SOLIDS: 19.42**  
**SOLVENT DENSITY: 8.06 VOC LE: 3.1 VOC AP: 1.1**  
**FLASH POINT: 100°F - 141°F H: 1 F: 2 R: 0 OSHA STORAGE: II**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

**WB1006™** Acrylic resin - waterborne, Mica, N-pentanol, N-propanol, Polyurethane resin, Propylene glycol methyl ether, Titanium dioxide, anatase(3.6%), Water  
**GAL WT: 8.82 WT PCT SOLIDS: 25.59 VOL PCT SOLIDS: 19.42**  
**SOLVENT DENSITY: 8.06 VOC LE: 3.1 VOC AP: 1.1**  
**FLASH POINT: 100°F - 141°F H: 1 F: 2 R: 0 OSHA STORAGE: II**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

**WB1007™** Acrylic resin - waterborne, Mica, N-pentanol, N-propanol, Polyurethane resin, Propylene glycol methyl ether, Titanium dioxide (rutile)(4.5%), Water  
**GAL WT: 8.83 WT PCT SOLIDS: 25.59 VOL PCT SOLIDS: 19.35**  
**SOLVENT DENSITY: 8.06 VOC LE: 3.1 VOC AP: 1.1**  
**FLASH POINT: 100°F - 141°F H: 1 F: 2 R: 0 OSHA STORAGE: II**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

**WB1008™** Acrylic resin - waterborne, Mica, N-pentanol, N-propanol, Polyurethane resin, Propylene glycol methyl ether, Titanium dioxide

(rutile)(5.2%), Water  
**GAL WT: 8.83 WT PCT SOLIDS: 25.59 VOL PCT SOLIDS: 19.29**  
**SOLVENT DENSITY: 8.06 VOC LE: 3.1 VOC AP: 1.1**  
**FLASH POINT: 100°F - 141°F H: 1 F: 2 R: 0 OSHA STORAGE: II**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

**WB1009™** Acrylic resin - waterborne, Mica, N-pentanol, N-propanol, Polyurethane resin, Propylene glycol methyl ether, Titanium dioxide(3.2%), Water  
**GAL WT: 8.81 WT PCT SOLIDS: 25.59 VOL PCT SOLIDS: 19.49**  
**SOLVENT DENSITY: 8.14 VOC LE: 3.1 VOC AP: 1.1**  
**FLASH POINT: 100°F - 141°F H: 1 F: 2 R: 0 OSHA STORAGE: II**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

**WB1010™** Acrylic resin - waterborne, Iron oxide-B, Mica, N-pentanol, N-propanol, Polyurethane resin, Propylene glycol methyl ether, Water  
**GAL WT: 8.83 WT PCT SOLIDS: 25.59 VOL PCT SOLIDS: 19.35**  
**SOLVENT DENSITY: 8.06 VOC LE: 3.0 VOC AP: 1.1**  
**FLASH POINT: 100°F - 141°F H: 1 F: 2 R: 0 OSHA STORAGE: II**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

**WB1011™** Acrylic resin - waterborne, Iron oxide-A, Mica, N-pentanol, N-propanol, Polyurethane resin, Propylene glycol methyl ether, Water  
**GAL WT: 8.82 WT PCT SOLIDS: 25.59 VOL PCT SOLIDS: 19.42**  
**SOLVENT DENSITY: 8.06 VOC LE: 3.1 VOC AP: 1.1**  
**FLASH POINT: 100°F - 141°F H: 1 F: 2 R: 0 OSHA STORAGE: II**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

**WB1012™** Acrylic resin - waterborne, Iron oxide-A, Mica, N-pentanol, N-propanol, Polyurethane resin, Propylene glycol methyl ether, Water  
**GAL WT: 8.82 WT PCT SOLIDS: 25.59 VOL PCT SOLIDS: 19.42**  
**SOLVENT DENSITY: 8.06 VOC LE: 3.0 VOC AP: 1.1**  
**FLASH POINT: 100°F - 141°F H: 1 F: 2 R: 0 OSHA STORAGE: II**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

**WB1013™** Acrylic resin - waterborne, Iron oxide-A, Mica, N-pentanol, N-propanol, Polyurethane resin, Propylene glycol methyl ether, Water  
**GAL WT: 8.84 WT PCT SOLIDS: 25.59 VOL PCT SOLIDS: 19.24**  
**SOLVENT DENSITY: 8.06 VOC LE: 3.0 VOC AP: 1.1**  
**FLASH POINT: 100°F - 141°F H: 1 F: 2 R: 0 OSHA STORAGE: II**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

**WB1014™** Acrylic resin - waterborne, Mica, N-pentanol, N-propanol, Polyurethane resin, Propylene glycol methyl ether, Titanium dioxide(4.6%), Water  
**GAL WT: 8.83 WT PCT SOLIDS: 25.59 VOL PCT SOLIDS: 19.35**  
**SOLVENT DENSITY: 8.06 VOC LE: 3.1 VOC AP: 1.1**  
**FLASH POINT: 100°F - 141°F H: 1 F: 2 R: 0 OSHA STORAGE: II**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

**WB1020™** Acrylic resin - waterborne, Aluminum oxide(6%\*), N-pentanol, N-propanol, Polyurethane resin, Propylene glycol methyl ether, Titanium dioxide (rutile)(1.8%), Water  
**GAL WT: 8.86 WT PCT SOLIDS: 25.59 VOL PCT SOLIDS: 19.04**  
**SOLVENT DENSITY: 8.06 VOC LE: 3.1 VOC AP: 1.1**  
**FLASH POINT: 100°F - 141°F H: 1 F: 2 R: 0 OSHA STORAGE: II**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

**WB1021™** Acrylic resin - waterborne, Aluminum oxide(5%\*), N-pentanol, N-propanol, Polyurethane resin, Propylene glycol methyl ether, Titanium dioxide (rutile)(3.3%), Water  
**GAL WT: 8.86 WT PCT SOLIDS: 25.59 VOL PCT SOLIDS: 19.08**  
**SOLVENT DENSITY: 8.06 VOC LE: 3.1 VOC AP: 1.1**  
**FLASH POINT: 100°F - 141°F H: 1 F: 2 R: 0 OSHA STORAGE: II**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

**WB1022™** Acrylic resin - waterborne, Aluminum oxide(3%\*), N-pentanol, N-propanol, Polyurethane resin, Propylene glycol methyl ether, Titanium dioxide (rutile)(4.9%), Water

**GAL WT: 8.87 WT PCT SOLIDS: 25.59 VOL PCT SOLIDS: 18.99**  
**SOLVENT DENSITY: 8.06 VOC LE: 3.1 VOC AP: 1.1**  
**FLASH POINT: 100°F - 141°F H: 1 F: 2 R: 0 OSHA STORAGE: II**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

**WB1023™** Acrylic resin - waterborne, Aluminum oxide(6%), N-pentanol, N-propanol, Polyurethane resin, Propylene glycol methyl ether, Titanium dioxide (rutile)(2.4%), Water  
**GAL WT: 8.86 WT PCT SOLIDS: 25.59 VOL PCT SOLIDS: 19.04**  
**SOLVENT DENSITY: 8.06 VOC LE: 3.1 VOC AP: 1.1**  
**FLASH POINT: 100°F - 141°F H: 1 F: 2 R: 0 OSHA STORAGE: II**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

**WB1024™** Acrylic resin - waterborne, Aluminum oxide(4%), Iron oxide-A, N-pentanol, N-propanol, Polyurethane resin, Propylene glycol methyl ether, Water  
**GAL WT: 8.88 WT PCT SOLIDS: 25.59 VOL PCT SOLIDS: 18.91**  
**SOLVENT DENSITY: 8.06 VOC LE: 3.1 VOC AP: 1.1**  
**FLASH POINT: 100°F - 141°F H: 1 F: 2 R: 0 OSHA STORAGE: II**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

**WB1025™** Acrylic resin - waterborne, Aluminum oxide(8%), N-pentanol, N-propanol, Polyurethane resin, Propylene glycol methyl ether, Water  
**GAL WT: 8.87 WT PCT SOLIDS: 25.59 VOL PCT SOLIDS: 18.95**  
**SOLVENT DENSITY: 8.06 VOC LE: 3.2 VOC AP: 1.1**  
**FLASH POINT: 100°F - 141°F H: 1 F: 2 R: 0 OSHA STORAGE: II**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

**WB1030™** Acrylic resin - waterborne, Aluminum(3%), Ethylene glycol monobutyl ether(1%), N-pentanol, N-propanol, Polyurethane resin, Propylene glycol methyl ether, Water  
**GAL WT: 8.49 WT PCT SOLIDS: 13.78 VOL PCT SOLIDS: 10.81**  
**SOLVENT DENSITY: 8.17 VOC LE: 3.6 VOC AP: 0.8**  
**FLASH POINT: 100°F - 141°F H: 2 F: 2 R: 1 OSHA STORAGE: II**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

**WB1031™** Acrylic resin, Acrylic resin - waterborne, Aluminum(5%), Ethylene glycol monobutyl ether(1%), Medium mineral spirits, N-pentanol, N-propanol, Polyurethane resin, Propylene glycol methyl ether, Water  
**GAL WT: 8.51 WT PCT SOLIDS: 19.20 VOL PCT SOLIDS: 14.52**  
**SOLVENT DENSITY: 7.98 VOC LE: 4.3 VOC AP: 1.6**  
**FLASH POINT: 100°F - 141°F H: 2 F: 2 R: 1 OSHA STORAGE: II**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

**WB1032™** Acrylic resin, Acrylic resin - waterborne, Aluminum(5%), Ethylene glycol monobutyl ether(1%), N-pentanol, N-propanol, Polyurethane resin, Propylene glycol methyl ether, Water  
**GAL WT: 8.52 WT PCT SOLIDS: 19.30 VOL PCT SOLIDS: 14.45**  
**SOLVENT DENSITY: 8.05 VOC LE: 4.3 VOC AP: 1.6**  
**FLASH POINT: 100°F - 141°F H: 2 F: 2 R: 1 OSHA STORAGE: II**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

**WB1033™** Acrylic resin, Acrylic resin - waterborne, Aluminum(5%), Isopropyl alcohol, N-pentanol, N-propanol, Polyurethane resin, Propylene glycol methyl ether, Water  
**GAL WT: 8.59 WT PCT SOLIDS: 19.35 VOL PCT SOLIDS: 14.20**  
**SOLVENT DENSITY: 7.94 VOC LE: 4.3 VOC AP: 1.6**  
**FLASH POINT: 100°F - 141°F H: 2 F: 2 R: 1 OSHA STORAGE: II**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

**WB1035™** Acrylic resin, Acrylic resin - waterborne, Aluminum(5%), Ethylene glycol monobutyl ether(1%), N-pentanol, N-propanol, Polyurethane resin, Propylene glycol methyl ether, Water  
**GAL WT: 8.58 WT PCT SOLIDS: 20.15 VOL PCT SOLIDS: 15.34**  
**SOLVENT DENSITY: 8.10 VOC LE: 3.8 VOC AP: 1.3**  
**FLASH POINT: 100°F - 141°F H: 2 F: 2 R: 1 OSHA STORAGE: II**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

**WB1037™** Acrylic resin, Acrylic resin - waterborne, Aluminum(5%),

Isopropyl alcohol, N-pentanol, N-propanol, Polyurethane resin, Propylene glycol methyl ether, Water

**GAL WT: 8.54 WT PCT SOLIDS: 21.13 VOL PCT SOLIDS: 16.30**  
**SOLVENT DENSITY: 8.05 VOC LE: 3.8 VOC AP: 1.4**  
**FLASH POINT: 100°F - 141°F H: 2 F: 2 R: 1 OSHA STORAGE: II**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

**WB1039™** Acrylic resin, Acrylic resin - waterborne, Aluminum(5%), Ethylene glycol monobutyl ether(1%), Medium mineral spirits, N-pentanol, N-propanol, Polyurethane resin, Propylene glycol methyl ether, Water  
**GAL WT: 8.60 WT PCT SOLIDS: 20.67 VOL PCT SOLIDS: 15.87**  
**SOLVENT DENSITY: 8.12 VOC LE: 3.7 VOC AP: 1.3**  
**FLASH POINT: 100°F - 141°F H: 2 F: 2 R: 1 OSHA STORAGE: II**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

**WB1041™** Acrylic resin, Acrylic resin - waterborne, Aluminum(7%), Medium mineral spirits, N-pentanol, N-propanol, Polyurethane resin, Propylene glycol methyl ether, Water  
**GAL WT: 8.68 WT PCT SOLIDS: 21.86 VOL PCT SOLIDS: 16.11**  
**SOLVENT DENSITY: 8.04 VOC LE: 3.7 VOC AP: 1.2**  
**FLASH POINT: 100°F - 141°F H: 2 F: 2 R: 1 OSHA STORAGE: II**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

**WB1050™** Acrylic resin (ts), Urea-formaldehyde condensation polymer, Water  
**GAL WT: 8.67 WT PCT SOLIDS: 15.50 VOL PCT SOLIDS: 12.08**  
**SOLVENT DENSITY: 8.37 VOC LE: 0.9 VOC AP: 0.1**  
**FLASH POINT: 141°F - 200°F H: 2 F: 2 R: 0 OSHA STORAGE: IIIA**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

**WB1078™** Acrylic resin, Acrylic resin - waterborne, Aluminum(4%), Hydrotreated heavy naphtha (petroleum), Iron oxide-A, N-pentanol, N-propanol, Polyurethane resin, Propylene glycol methyl ether, Water  
**GAL WT: 8.45 WT PCT SOLIDS: 18.61 VOL PCT SOLIDS: 13.78**  
**SOLVENT DENSITY: 7.93 VOC LE: 4.4 VOC AP: 1.6**  
**FLASH POINT: 100°F - 141°F H: 1 F: 2 R: 1 OSHA STORAGE: II**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

**WB20™** Acrylic polymer-B, Acrylic resin (ts), C.i. pigment violet 23, Dipropylene glycol methyl ether, Polyurethane resin, Water  
**GAL WT: 8.52 WT PCT SOLIDS: 10.87 VOL PCT SOLIDS: 8.58**  
**SOLVENT DENSITY: 8.29 VOC LE: 2.1 VOC AP: 0.2**  
**FLASH POINT: 141°F - 200°F H: 0 F: 2 R: 0 OSHA STORAGE: IIIA**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

**WB2010™** Acetone, Acrylic resin - waterborne, N-pentanol, Polyurethane resin, Water  
**GAL WT: 8.46 WT PCT SOLIDS: 23.18 VOL PCT SOLIDS: 21.21**  
**SOLVENT DENSITY: 8.25 VOC LE: 1.8 VOC AP: 0.5**  
**FLASH POINT: 141°F - 200°F H: 2 F: 2 R: 1 OSHA STORAGE: IIIA**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

**WB2020™** Acrylic resin - waterborne, N-pentanol, Polyurethane resin, Water  
**GAL WT: 8.40 WT PCT SOLIDS: 14.38 VOL PCT SOLIDS: 13.06**  
**SOLVENT DENSITY: 8.27 VOC LE: 1.9 VOC AP: 0.3**  
**FLASH POINT: 141°F - 200°F H: 1 F: 2 R: 0 OSHA STORAGE: IIIA**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

**WB2030™** Acetone, Acrylic resin - waterborne, N-pentanol, Polyurethane resin, Water  
**GAL WT: 8.46 WT PCT SOLIDS: 23.53 VOL PCT SOLIDS: 21.52**  
**SOLVENT DENSITY: 8.24 VOC LE: 1.9 VOC AP: 0.6**  
**FLASH POINT: 141°F - 200°F H: 2 F: 2 R: 1 OSHA STORAGE: IIIA**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

**WB2040™** Acrylic resin - waterborne, N-pentanol, Polypropylene glycol, Polyurethane resin, Synthetic magnesium silicate, Water  
**GAL WT: 8.40 WT PCT SOLIDS: 17.34 VOL PCT SOLIDS: 15.56**

**SOLVENT DENSITY: 8.22 VOC LE: 2.3 VOC AP: 0.5**  
**FLASH POINT: 100°F - 141°F H: 2 F: 2 R: 1 OSHA STORAGE: II**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

**WB2090™** Acrylic resin (ts), Acrylic resin - waterborne, N-pentanol, Polyurethane resin, Urea-formaldehyde condensation polymer, Water  
**GAL WT: 8.50 WT PCT SOLIDS: 21.65 VOL PCT SOLIDS: 19.42**  
**SOLVENT DENSITY: 8.18 VOC LE: 1.8 VOC AP: 0.5**  
**FLASH POINT: 141°F - 200°F H: 1 F: 2 R: 0 OSHA STORAGE: IIIA**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

**WB21™** Acrylic polymer-B, Acrylic resin (ts), Anthraquinone pigment, Water  
**GAL WT: 8.72 WT PCT SOLIDS: 18.07 VOL PCT SOLIDS: 13.82**  
**SOLVENT DENSITY: 8.28 VOC LE: 1.3 VOC AP: 0.2**  
**FLASH POINT: 141°F - 200°F H: 1 F: 2 R: 0 OSHA STORAGE: IIIA**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

**WB24™** Acrylic polymer-B, Acrylic resin (ts), Isopropyl alcohol, Phthalocyanine blue pigment, Water  
**GAL WT: 8.90 WT PCT SOLIDS: 22.85 VOL PCT SOLIDS: 17.11**  
**SOLVENT DENSITY: 8.27 VOC LE: 1.3 VOC AP: 0.3**  
**FLASH POINT: 141°F - 200°F H: 1 F: 2 R: 0 OSHA STORAGE: IIIA**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

**WB25™** Acrylic polymer-B, Acrylic resin (ts), Phthalocyanine blue pigment, Polyurethane resin, Water  
**GAL WT: 8.64 WT PCT SOLIDS: 12.73 VOL PCT SOLIDS: 9.22**  
**SOLVENT DENSITY: 8.29 VOC LE: 1.4 VOC AP: 0.2**  
**FLASH POINT: 141°F - 200°F H: 1 F: 2 R: 0 OSHA STORAGE: IIIA**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

**WB26™** Acrylic resin - waterborne, N-pentanol, Polyurethane resin, Water  
**GAL WT: 8.42 WT PCT SOLIDS: 13.52 VOL PCT SOLIDS: 11.96**  
**SOLVENT DENSITY: 8.22 VOC LE: 2.1 VOC AP: 0.4**  
**FLASH POINT: 141°F - 200°F H: 0 F: 2 R: 0 OSHA STORAGE: IIIA**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

**WB27™** Acrylic resin (ts), Dipropylene glycol methyl ether, Dispersing agent, Phthalocyanine blue pigment, Polyurethane resin, Water  
**GAL WT: 8.68 WT PCT SOLIDS: 15.87 VOL PCT SOLIDS: 11.81**  
**SOLVENT DENSITY: 8.27 VOC LE: 2.6 VOC AP: 0.5**  
**FLASH POINT: 141°F - 200°F H: 1 F: 2 R: 0 OSHA STORAGE: IIIA**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

**WB28™** Acrylic resin (ts), Copper phthalocyanine, Dipropylene glycol methyl ether, Dispersing agent, Polyurethane resin, Proprietary copper compound(2%), Water  
**GAL WT: 8.93 WT PCT SOLIDS: 25.44 VOL PCT SOLIDS: 19.77**  
**SOLVENT DENSITY: 8.29 VOC LE: 1.7 VOC AP: 0.4**  
**FLASH POINT: 141°F - 200°F H: 2 F: 2 R: 0 OSHA STORAGE: IIIA**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

**WB30™** Phthalocyanine green, Polyurethane resin, Water  
**GAL WT: 8.83 WT PCT SOLIDS: 15.84 VOL PCT SOLIDS: 10.53**  
**SOLVENT DENSITY: 8.29 VOC LE: 1.2 VOC AP: 0.1**  
**FLASH POINT: 141°F - 200°F H: 1 F: 2 R: 0 OSHA STORAGE: IIIA**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

**WB31™** Acrylic resin - waterborne, N-pentanol, Polyurethane resin, Water  
**GAL WT: 8.42 WT PCT SOLIDS: 13.31 VOL PCT SOLIDS: 11.69**  
**SOLVENT DENSITY: 8.23 VOC LE: 2.1 VOC AP: 0.4**  
**FLASH POINT: 141°F - 200°F H: 0 F: 2 R: 0 OSHA STORAGE: IIIA**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

**WB32™** Acrylic polymer-B, Acrylic resin (ts), Dipropylene glycol methyl ether, Phthalocyanine green pigment, Polyurethane resin, Water  
**GAL WT: 9.33 WT PCT SOLIDS: 23.66 VOL PCT SOLIDS: 14.11**

**SOLVENT DENSITY: 8.26 VOC LE: 1.9 VOC AP: 0.4**  
**FLASH POINT: 141°F - 200°F H: 1 F: 2 R: 0 OSHA STORAGE: IIIA**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

**WB33™** Acrylic polymer-B, Acrylic resin (ts), Melamine resin, Nickel azo complex (py 150)(4.8%\*®), Water  
**GAL WT: 8.71 WT PCT SOLIDS: 15.82 VOL PCT SOLIDS: 11.74**  
**SOLVENT DENSITY: 8.29 VOC LE: 1.4 VOC AP: 0.2**  
**FLASH POINT: 141°F - 200°F H: 1 F: 2 R: 0 OSHA STORAGE: IIIA**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

**WB41™** Acrylic polymer-B, Acrylic resin (ts), Dipropylene glycol methyl ether, Isopropyl alcohol, Quinophthalone yellow pigment, Water  
**GAL WT: 9.88 WT PCT SOLIDS: 37.70 VOL PCT SOLIDS: 25.61**  
**SOLVENT DENSITY: 8.25 VOC LE: 1.3 VOC AP: 0.4**  
**FLASH POINT: 141°F - 200°F H: 1 F: 2 R: 0 OSHA STORAGE: IIIA**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

**WB43™** Acrylic polymer-B, Acrylic resin (ts), Water, Yellow pigment  
**GAL WT: 9.13 WT PCT SOLIDS: 28.32 VOL PCT SOLIDS: 21.11**  
**SOLVENT DENSITY: 8.29 VOC LE: 0.7 VOC AP: 0.2**  
**FLASH POINT: 141°F - 200°F H: 1 F: 2 R: 0 OSHA STORAGE: IIIA**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

**WB45™** Polyurethane resin, Tetrachloroisosolinone yellow pigment, Water  
**GAL WT: 8.77 WT PCT SOLIDS: 15.84 VOL PCT SOLIDS: 11.19**  
**SOLVENT DENSITY: 8.29 VOC LE: 1.1 VOC AP: 0.1**  
**FLASH POINT: 141°F - 200°F H: 1 F: 2 R: 0 OSHA STORAGE: IIIA**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

**WB46™** Dipropylene glycol methyl ether, Isoindolinone pigment, Polyurethane resin, Water  
**GAL WT: 9.26 WT PCT SOLIDS: 31.75 VOL PCT SOLIDS: 23.69**  
**SOLVENT DENSITY: 8.25 VOC LE: 1.8 VOC AP: 0.5**  
**FLASH POINT: 141°F - 200°F H: 1 F: 2 R: 0 OSHA STORAGE: IIIA**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

**WB53™** Acrylic resin (ts), Dipropylene glycol methyl ether, Monoazo pigment, Water  
**GAL WT: 9.44 WT PCT SOLIDS: 34.03 VOL PCT SOLIDS: 24.90**  
**SOLVENT DENSITY: 8.28 VOC LE: 1.0 VOC AP: 0.3**  
**FLASH POINT: 141°F - 200°F H: 1 F: 2 R: 0 OSHA STORAGE: IIIA**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

**WB60™** Acrylic polymer-B, Acrylic resin (ts), C.i. pigment red 254, Dipropylene glycol methyl ether, Polyurethane resin, Water  
**GAL WT: 9.57 WT PCT SOLIDS: 39.57 VOL PCT SOLIDS: 29.93**  
**SOLVENT DENSITY: 8.25 VOC LE: 1.5 VOC AP: 0.5**  
**FLASH POINT: 141°F - 200°F H: 0 F: 2 R: 0 OSHA STORAGE: IIIA**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

**WB62™** Acrylic polymer-B, Acrylic resin (ts), Quinacridone pigment, Water  
**GAL WT: 8.66 WT PCT SOLIDS: 15.68 VOL PCT SOLIDS: 12.05**  
**SOLVENT DENSITY: 8.28 VOC LE: 1.7 VOC AP: 0.3**  
**FLASH POINT: 141°F - 200°F H: 1 F: 2 R: 0 OSHA STORAGE: IIIA**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

**WB63™** Dispersing agent, Perylene pigment, Water  
**GAL WT: 8.71 WT PCT SOLIDS: 14.09 VOL PCT SOLIDS: 10.08**  
**SOLVENT DENSITY: 8.31 VOC LE: 1.2 VOC AP: 0.1**  
**FLASH POINT: 141°F - 200°F H: 1 F: 2 R: 0 OSHA STORAGE: IIIA**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

**WB64™** Acrylic resin (ts), Pigment red 202, Polyurethane resin, Quinacridone pigment, Water  
**GAL WT: 8.62 WT PCT SOLIDS: 12.61 VOL PCT SOLIDS: 9.44**  
**SOLVENT DENSITY: 8.33 VOC LE: 1.1 VOC AP: 0.1**



**FLASH POINT: 141°F - 200°F H: 1 F: 2 R: 0 OSHA STORAGE: IIIA**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALY REACTIVE: NO**

The information on this Material Safety Data Sheet relates only to the specific material designated herein and does not relate to use in combination with any other material or in any process.

**WB65™** Acrylic resin - waterborne, N-pentanol, Polyurethane resin, Water  
**GAL WT: 8.42 WT PCT SOLIDS: 12.67 VOL PCT SOLIDS: 11.13**  
**SOLVENT DENSITY: 8.23 VOC LE: 2.1 VOC AP: 0.3**  
**FLASH POINT: 141°F - 200°F H: 0 F: 2 R: 0 OSHA STORAGE: IIIA**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALY REACTIVE: NO**

Product Manager: Refinish Sales  
Prepared by: Y. B. Yarbrough

**WB67™** Acrylic resin (ts), Polyurethane resin, Quinacridone pigment, Water  
**GAL WT: 8.94 WT PCT SOLIDS: 25.30 VOL PCT SOLIDS: 19.59**  
**SOLVENT DENSITY: 8.29 VOC LE: 0.7 VOC AP: 0.2**  
**FLASH POINT: 141°F - 200°F H: 1 F: 2 R: 0 OSHA STORAGE: IIIA**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALY REACTIVE: NO**

**WB68™** Acrylic polymer-B, Acrylic resin (ts), Quinacridone pigment, Water  
**GAL WT: 8.64 WT PCT SOLIDS: 15.29 VOL PCT SOLIDS: 11.72**  
**SOLVENT DENSITY: 8.29 VOC LE: 1.4 VOC AP: 0.2**  
**FLASH POINT: 141°F - 200°F H: 1 F: 2 R: 0 OSHA STORAGE: IIIA**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALY REACTIVE: NO**

**WB82™** Acrylic resin (ts), Dipropylene glycol methyl ether, Iron hydroxide, Polyurethane resin, Water  
**GAL WT: 9.31 WT PCT SOLIDS: 21.76 VOL PCT SOLIDS: 12.40**  
**SOLVENT DENSITY: 8.28 VOC LE: 2.0 VOC AP: 0.3**  
**FLASH POINT: 141°F - 200°F H: 1 F: 2 R: 0 OSHA STORAGE: IIIA**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALY REACTIVE: NO**

**WB84™** Acrylic resin (ts), Iron oxide-A, Polyurethane resin, Water  
**GAL WT: 9.51 WT PCT SOLIDS: 19.30 VOL PCT SOLIDS: 7.69**  
**SOLVENT DENSITY: 8.30 VOC LE: 1.8 VOC AP: 0.2**  
**FLASH POINT: 141°F - 200°F H: 1 F: 2 R: 0 OSHA STORAGE: IIIA**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALY REACTIVE: NO**

**WB90™** 2-amino-2-methyl-1-propanol, Acrylic polymer-B, Acrylic resin (ts), Dipropylene glycol methyl ether, Isopropyl alcohol, Light yellow lemon yellow oxide pigment, Rheology agent, Water  
**GAL WT: 9.02 WT PCT SOLIDS: 19.18 VOL PCT SOLIDS: 11.43**  
**SOLVENT DENSITY: 8.21 VOC LE: 3.1 VOC AP: 0.6**  
**FLASH POINT: 141°F - 200°F H: 1 F: 2 R: 0 OSHA STORAGE: IIIA**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALY REACTIVE: NO**

**WB91™** 2-amino-2-methyl-1-propanol, Acrylic polymer-A, Iron oxide-A, Polyurethane resin, Water  
**GAL WT: 8.89 WT PCT SOLIDS: 19.57 VOL PCT SOLIDS: 14.08**  
**SOLVENT DENSITY: 8.28 VOC LE: 1.3 VOC AP: 0.2**  
**FLASH POINT: 141°F - 200°F H: 1 F: 2 R: 0 OSHA STORAGE: IIIA**  
**TSCA STATUS: In Compliance PHOTO-CHEMICALY REACTIVE: NO**

**Footnotes:**

**TSCA: in compliance** = In compliance with TSCA Inventory requirements for commercial purposes.

**ACGIH** = American Conference of Governmental Industrial Hygienists.

**IARC** = International Agency for Research on Cancer.

**NTP** = National Toxicology Program.

**OSHA** = Occupational Safety and Health Administration.

**PNOR** = Particles not otherwise regulated.

**PNOC** = Particles not otherwise classified.

**STEL** = Short term exposure limit.

**TWA** = Time-weighted average.

**TM** = Is a Trademark of E.I. DuPont de Nemours Co.

\* = Section 313 Supplier Notification: These chemicals are subject to the reporting requirements of Section 313 of the Emergency planning and Right-to-Know act of 1986 and of 40 CFR 372.

@ = Listed as a Clean Air Act Hazardous Air Pollutant.

# = EPCRA Section 302 - Extremely hazardous substances.

**Notice:**