



## The premiere resin for:

- **Filleting**
- **Laminating**
- **Gluing**

We **highly** recommend this resin for general purpose gluing applications where wet-out of fiberglass is not a consideration, and for all your filleting and fairing needs.

F.L.A.G. Resin is a "medium" body resin specifically designed to perform as an adhesive and structural laminating foundation. The medium viscosity allows for the incorporation of fillers when fairing putties, gluing slurries and filleting systems are required. F.L.A.G. is more reactive than our Low Viscosity Resin when mixed with Medium Hardener. This keeps fillets and fairing from slumping. F.L.A.G Resin is next day sandable when cured at 60 degrees F. and higher with Medium Hardener. F.L.A.G Resin may be used with all MAS Hardeners, however, for filled applications we recommend our Medium Hardener.

Measured Properties		Impirical Calculations or Physical Properties	
Resin Viscosity	3000-3400 cps	Hardness	Please Call Factory For More Information.
Color	1 Gardner Max	Tensile Strength	
EEW	190-200	Tensile Elogation	
Tg	140°F	Compressive Strength	
Mix Ratio	2:1 Resin:Hardener		
Peak Exotherm (30g batch)	360°F		
Pot Life (30g batch)	15 minutes		

**Physical properties are subject to change based on formula updates. Please contact factory for more information.**

We highly recommend this product for your filleting and fairing applications.