


Standex® Charts & Systems

Blending-in with Standox Basecoat



Working Process: Blending-in with Standox Basecoat	
Substrates:	✓ For preparation of the repair areas, see Painting System S1. Keep the surface for priming with Filler as small as possible.
Substrate Preparation: 	Sand the repair area for application of Standex Basecoat with P800. Sand surrounding blend areas with P1200-P1500 (wet or dry). Then, finish the entire surface with a gold scuff pad in conjunction with Standohyd® Sanding Paste. (Article No. 14670). Trizact P1000 may also be used. For substrate cleaning, see Standex Painting System S1.
Painting:	• Apply Standex Basecoat Colorless, if necessary. • Apply Basecoat to the repair area. Taper as necessary. Ensure coverage has been reached. • Dilute Standex Basecoat to 17s/DIN 4 mm or mix ready-to-spray Standex Basecoat 2:1 with Standex Basecoat Colorless. Reduce spray pressure to 15-25 psi (1-1.5 bar). Use the droplet technique, if necessary. • Apply to the repair area and overlap each spray pass over a larger area. • Apply Standocryl® 2K Clear to the entire repair panel(s) to achieve 2.0-2.4 mils. • For Blending-in Standocryl 2K Clear, see System S8.

Important Legislative Remarks:

- For industrial use only by professional, trained painters. Not for sale to or use by the general public. Before using, read and follow all label and MSDS precautions. If mixed with other components, mixture will have hazards of all components. Ready to use paint materials containing isocyanates can cause irritation of the respiratory organs and hypersensitive reactions. Asthma sufferers, those with allergies and anyone with a history of respiratory complaints must not be asked to work with products containing isocyanates. Do not sand, flame cut, braze or weld dry coating without a NIOSH approved air purifying respirator with particulate filters or appropriate ventilation, and gloves.
- Any analytical results set forth herein do not constitute a warranty of specific product features or of the product's suitability for a specific purpose. All products are sold pursuant to our general conditions of sale. We hereby disclaim all warranties and representations, express or implied, with respect to this product, including any warranty of merchantability or fitness for a particular purpose. This product is protected by patent law, trademark law, copyright law, international treaties and/or other applicable law. All rights reserved. Unauthorized sale, manufacturing or use may result in civil and criminal penalties.