


Working Process: Blending-in with Standohyd Basecoat	
Substrates:	<ul style="list-style-type: none"> ✓ For preparation of the repair areas, see Painting System S1. Keep the surface for priming with Filler as small as possible.
 Substrate Preparation:	<p>Sand the repair area for application of Standohyd Basecoat with P800. Sand surrounding blend areas with P1200-P1500 (wet or dry). Then, finish the entire surface with a gold scuff pad in conjunction with Standohyd[®] Sanding Paste (14670). Trizact P1000 may also be used.</p> <p>For substrate cleaning, see Standex Painting System S1. Final cleaning must be done with a Standohyd Cleaner.</p>
Painting:	<ul style="list-style-type: none"> • Apply Standohyd Colorblend (80045-TDS 806), if necessary. • Apply Standohyd Basecoat with reduced viscosity (18-22 s/DIN4) and reduced spray pressure (15-25 psi (1-1.5 bar)) with several spray passes and even out spray pattern to achieve opacity. After each spray pass, blow dry with an air gun. Flash-off matt. • Apply 1 spray pass Standocryl[®] 2K Clear on Standohyd Basecoat blending-in area. After flash-off time, apply Standocryl 2K Clear over the whole panel to achieve 2.0-2.4 mils.

Important Technical Remarks:

- If necessary, mix 1:1 with **Standohyd** Colorblend (80045) to make the final spray passes of the blend-in procedure.
- Remove overspray carefully from entire area with a tack rag after a final flash off to a matt finish.
- For blends, light coats are still the preferred method. For difficult colors however, the wet bed - 2 gun method is the best. Apply a coat of the blender to the panel first, then immediately blend into the wet bed with either the color thinned to 20 seconds, or thinned 1:1 with the blender. Best results are achieved with the blend mix as a drop coat only on the transition zone, not over the entire repair/blend area.
- For full panels, use a true mist coat followed by a closed coat with a final covering coat as a control coat.

Important Legislative Remarks:

- **For industrial use only by professional, trained painters. Not for sale to or use by the general public. Before using, read and follow all label and MSDS precautions. If mixed with other components, mixture will have hazards of all components. Ready to use paint materials containing isocyanates can cause irritation of the respiratory organs and hypersensitive reactions. Asthma sufferers, those with allergies and anyone with a history of respiratory complaints must not be asked to work with products containing isocyanates. Do not sand, flame cut, braze or weld dry coating without a NIOSH approved air purifying respirator with particulate filters or appropriate ventilation, and gloves.**
- Any analytical results set forth herein do not constitute a warranty of specific product features or of the product's suitability for a specific purpose. All products are sold pursuant to our general conditions of sale. We hereby disclaim all warranties and representations, express or implied, with respect to this product, including any warranty of merchantability or fitness for a particular purpose. This product is protected by patent law, trademark law, copyright law, international treaties and/or other applicable law. All rights reserved. Unauthorized sale, manufacturing or use may result in civil and criminal penalties.