


Standosoft® Fineplastic



Ordering Information:		
1 kg	Standosoft Fineplastic	020 12251
50 g	Hardener Paste	020 14262

Features:

- ✧ Fine polyester body filler/ putty
- ✧ Easy to spread
- ✧ Pore-free, fine surface
- ✧ Suitable for plastic

Working Process: Fine Putty	
Substrates:	
<ul style="list-style-type: none"> ✓ Through-hardened, sanded paintwork ✓ Bare steel, GRP and aluminum, sanded ✓ Standex Polyester Stopper ✓ Through-hardened 2K Filler, sanded ✓ Primed plastic 	
	For substrate preparation information see Standex Painting System S1!
	3% Standex Hardener Paste Pot life 4-5 min / 68°F (20°C)
	Apply stopper.
	20-30 min/ 68°F (20°C)
	Short wave 2-3 min Medium wave 5-7 min (see Painting System S10)
	Dry sand P220-P400
	Standex Primers and Primer Fillers

Standosoft[®] Fineplastic

Important Technical Remarks:

- Do not apply over Etch Primers, 1K Primer Fillers, or critical substrates. A critical substrate is any substrate that fails a 2K solvent test and that will affect adhesion.
- Do not apply at temperatures below 50°F (10°C). This product will not cure at temperatures below this level.
- Mix the 3% **Stadox** Hardener paste with the stopper well. Mix correctly to avoid staining of the topcoat finish.
- Do not apply to galvanized substrates. Pre-prime with **Stadox** EP Precoat.
- This product can be applied over primer on plastic substrates.

Important Legislative Remarks:

- This product is not regulated under air quality regulations. Please see the **Stadox** MSDS or Master Values List for any product related value information.
- Hardener paste contains organic peroxide and is corrosive. If Hardener paste comes in contact with the skin, wipe off immediately and wash with soap and water. After eye contact, irrigate copiously with a 2% aqueous sodium carbonate solution or water and seek medical advice.
- **For industrial use only by professional, trained painters. Not for sale to or use by the general public. Before using, read and follow all label and MSDS precautions. If mixed with other components, mixture will have hazards of all components. Do not sand, flame cut, braze or weld dry coating without a NIOSH approved air purifying respirator with particulate filters or appropriate ventilation, and gloves.**
- Any analytical results set forth herein do not constitute a warranty of specific product features or of the product's suitability for a specific purpose. All products are sold pursuant to our general conditions of sale. We hereby disclaim all warranties and representations, express or implied, with respect to this product, including any warranty of merchantability or fitness for a particular purpose. This product is protected by patent law, trademark law, copyright law, international treaties and/or other applicable law. All rights reserved. Unauthorized sale, manufacturing or use may result in civil and criminal penalties.